

Thermo-Responsive Polymer Blends for Minimally Invasive Medical Procedures

Tanmay Mehta^{1,*}, Anil Bhattad², Anup Patil³

Abstract

Thermo-responsive polymer blends have become a key new class of biomaterials for the minimally invasive medical procedure. They offer precision, flexibility and greater patient safety. These smart materials undergo a change of physical/ mechanical properties relative to temperature difference in the body, limiting tissue trauma and increasing effectiveness of the procedure. Their adjustable sol–gel behavior, shape-memory effects, and reversible volume change provide an opportunity for their precise delivery through catheters, needles, or endoscopes, followed by their solidification or expansion, contraction, or conformance to anatomy at body temperature. Recent advances in polymer chemistry and nanotechnology and molecular engineering have increased their clinical use. Today, thermo-responsive blends are the topic of research in the fields of embolization, local drug delivery, tissue sealing, stent deployment, hemostasis, adhesion prevention and regenerative scaffolding. By using a combination of hydrogels (to be biocompatible), elastomers (to be flexible) and crystalline polymers (to have a structural memory), clinicians will be able to create transition temperatures, mechanical properties and degradation rates in materials. These systems also allow dynamic response in the body to support real-time adaptability in endovascular and laparoscopic processes. The addition of imaging agents, nanoparticles and bioactive compounds further enhances the function and precision. As healthcare progresses into a rapid, complication-free direction, thermos responsive polymer blends play an important role in safer and more efficient results. This review presents the current progress, design principles, clinical opportunities, and future issues associated with the use of these blends in the minimally invasive procedure.

Keywords: Thermo-responsive polymers, polymer blends, minimally invasive procedures, shape memory materials, smart hydrogels, temperature responsive biomaterials, biomedical polymers, injectable systems

*Author for Correspondence

Tanmay Mehta

E-mail: tanmaymehtakvv@zohomail.in

¹Assistant Professor, Department of Surgery, Krishna Vishwa Vidyapeeth (Deemed to Be University), Karad, Maharashtra, India

²Professor, Department of Medicine, Krishna Institute of Medical Sciences, Krishna Vishwa Vidyapeeth (Deemed to Be University), Karad, Maharashtra, India

³Associate Professor, Department of Pharmacology, Krishna Institute of Pharmacy, Krishna Vishwa Vidyapeeth (Deemed to Be University), Karad, Maharashtra, India

Received Date: July 13, 2026

Accepted Date: August 18, 2026

Published Date: August 26, 2026

Citation: Tanmay Mehta, Anil Bhattad, Anup Patil. Thermo-Responsive Polymer Blends for Minimally Invasive Medical Procedures. Journal of Polymer & Composites. 2026; 14(Special Issue 4): S323–S330p.

INTRODUCTION

Minimally invasive procedures are now a leading force in the clinical setting because of the reduced tissue damage, decreased length of stay in the hospital, and accelerated recovery time. Advances in materials science and in particular smart biomaterials sensitive to body stimuli have led to this change. Thermo-responsive polymer blends stand out by their predictable way of bodily temperature transformation. Their transitions are especially useful for catheter, endoscopic and percutaneous interventions, sol–gel conversion, shape recovery, swelling or deswelling and developments of mechanical strength [1].

Thermo-responsive polymers, such as poly(N-isopropylacrylamide) (PNIPAAm), poly(ϵ -caprolactone)

(PCL), polyethylene glycol (PEG)-based systems, and poloxamers, are extensively explored for biomedical applications and are biocompatible and tunable materials [2]. When mixed together, instead of taking them alone, their properties can be adapted to specific clinical needs. Blending makes it possible to control the crystallinity, the hydrophilicity, the rate of degradation, the mechanical performance, and the transition temperature. As a result, thermo-responsive polymer blends are being designed for an increasing number of minimally invasive procedures such as embolization therapy, localized drug delivery, hemostasis, bone defect filling, intravascular device deployment, and tissue regeneration scaffolds [3].

Thermo-responsive polymer blends have attracted considerable attention because they provide a unique combination of injectability, adaptability, and controlled responsiveness that cannot be achieved using conventional biomaterials [4]. By carefully selecting and blending polymers with complementary physicochemical properties, researchers can tailor phase transition behavior, gelation kinetics, mechanical strength, and degradation profiles to meet the specific requirements of different minimally invasive medical procedures. These materials can be administered in a minimally invasive manner through catheters, needles, or endoscopic devices and subsequently undergo temperature-induced transformation at the target site, forming stable structures that support therapeutic functions.

Their ability to conform to irregular anatomical spaces while minimizing surgical trauma makes them particularly valuable for localized drug delivery, tissue sealing, embolization, wound healing, orthopedic defect repair, and regenerative medicine. Furthermore, recent progress in blend optimization has improved their stability, biocompatibility, and functional performance, enabling more reliable clinical outcomes [5]. As research continues to address current limitations related to mechanical durability, degradation control, and long-term biological interactions, thermo-responsive polymer blends are expected to play an increasingly important role in the advancement of safe, effective, and patient-centered minimally invasive medical procedures.

This review aims at the design strategies and mechanisms, clinical applications, problems, and future trends of thermo-responsive polymer blends for minimally invasive procedures. It gives an overall overview of the latest developments with particular focus on innovations in blend chemistry, nanocomposite engineering and bio functional integration.

THERMO-RESPONSIVE BEHAVIOR IN POLYMER SYSTEMS

Fundamental Mechanisms

Thermotropic (metaplasia) response: Thermotropic. Responsive polymers contain a critical transition temperature upon which the polymer undergoes substantial change in solubility, phase or mechanical properties. In the case of aqueous media, such changes are usually described by either a lower critical solution temperature (LCST) or upper critical solution temperature (UCST). Polymers exhibiting LCST behavior dissolve below the T_c and become phase-separated or collapsed above T_c , which makes them interesting candidates for medical applications with the body temperature (~37 °C). Before delivering this talk, I will clarify (submitted term paper), I had a loose use of “phase-separated” in the first paragraph, but under the right conditions polymers – such as micelles in water – can form lamellar-phase-separated structure with a radius of about 5 nm [6].

Blending enables the fine-tunings of the transition temperature, depending on the reduction of the hydrophilic to hydrophobic ratio. For example, addition of PEG to PNIPAAm leads to increase of hydrophilicity, which weakly shifts the LCST, up or down depending on composition [7]. Likewise, combining PCL or PLA with shape-memory elastomers yields materials that heal their permanent shape at exactly the correct physiological temperatures, and which are, therefore, suitable for intravascular and soft-tissue interventions [8].

Sol–Gel Transition Behavior

Injectable thermo-gelling polymers are very valuable for minimally invasive procedures. These polymers exist at room temperatures as low viscosity sol, but rapidly become a gel in situ, when

exposed to the warm tissue. The classic examples are the poloxamers (Pluronic(R)), more recently developed are engineered copolymers of PEG and polyesters with higher stability and mechanical strength [9]. By combining various thermo-responsive ingredients, researchers can manage the rate of gelation, gel stiffness and gel degradation time, producing embolization agents, tissue follower or drug release depots.

Shape-Memory Effect

Shape-memory polymers (SMPs) memorize a temporary shape or shape at a given temperature above a transition point at which they regain a permanent shape when heated. Mixing SMPs with Hydrogels or Elastomers makes them less brittle and more elastic and responsive. SMP blends have been used to deliver stents, occlusion devices, and scaffolds which expand, or unfold, at body temperature after minimally invasive delivery [10].

Swelling and Deswelling Behavior

The swelling and deswelling behavior of thermo-responsive polymer blends is another important mechanism that supports their application in minimally invasive medical procedures. These polymers undergo reversible changes in water absorption in response to temperature variations, leading to controlled expansion or contraction of the polymer network. Below the critical transition temperature, hydrophilic interactions dominate, allowing the polymer matrix to absorb water and swell [11]. Above the transition temperature, hydrophobic interactions become predominant, resulting in water expulsion and polymer shrinkage. This reversible behavior can be precisely adjusted by blending hydrophilic polymers, such as polyethylene glycol (PEG) with more hydrophobic components including poly(ϵ -caprolactone) (PCL) or poly(lactic acid) (PLA), enabling fine control over swelling ratio, mechanical stability, and diffusion characteristics. In minimally invasive procedures, this property facilitates controlled drug release, improves tissue adhesion, enhances defect filling, and provides mechanical support within irregular anatomical sites [12].

POLYMER BLENDS IN THERMO-RESPONSIVE BIOMEDICAL APPLICATIONS

Poly(N-Isopropylacrylamide)-Based Blends

NIPAAm is one of the best studied thermo-responsive polymers. It is LCST of near 32°C makes it ideal for those systems which require gel or shrink at a little below or above room temperature. Blends with chitosan, PEG, hyaluronic acid and polyurethane enhance mechanical integrity, biocompatibility and adjust transition behavior [13]. PNIPAAm blends are used for injectable scaffolds, endoscopic sealants and catheter delivered drug reservoirs.

Poloxamer-Based Blends

Poloxamers are reversible sol–gel transitions through the formation and packing of micelles. When combined with some natural polymer, such as alginate, chitosan or gelatin, their mucoadhesive, mechanical and rheological properties are improved. These systems of hybrid technology are evaluated as part of an intranasal drug delivery, endoscopic hemostasis and as anti-adhesion barriers in laparoscopic surgery [14].

Poly(ϵ -Caprolactone)-Containing Blends

PCL, a semi-crystal biodegradable polyester, has high melting point close to the body temperature and is thus one of the considered candidates for thermo-responsive SMP system. The combination with urethane-based elastomers, poly (ethylene glycol) (PEG) or polydioxane (PDO) will make it a blend with good structural memory and variable degradation. Such materials are used as self-expanding stents, fracture fixation devices and controlled-release depots, which are delivered minimally invasively [15].

Poly (Ethylene Glycol) (PEG)-Based Blends

Poly (ethylene glycol) (PEG) is widely incorporated into thermo-responsive polymer blends because of its excellent biocompatibility, hydrophilicity, and low toxicity. When blended with Niam, PCL, or

biodegradable polyesters, PEG improves gelation behavior, mechanical flexibility, and degradation characteristics. These blends are commonly used as injectable hydrogels, localized drug delivery systems, tissue adhesives, and regenerative scaffolds. Their temperature-responsive behavior enables minimally invasive administration followed by in situ gel formation, providing sustained therapeutic effects and improved tissue integration [16].

Multi-Component Polymer Blends

Multi-component thermo-responsive polymer blends combine synthetic polymers, natural biomaterials, and functional additives to enhance mechanical strength, biodegradability, and biological performance. These blends allow precise control of gelation, swelling, and degradation while maintaining excellent biocompatibility. They have shown promising applications in embolization therapy, tissue engineering, wound healing, localized drug delivery, and minimally invasive implantable devices, offering improved adaptability and therapeutic efficiency in clinical practice [17].

Natural Polymer Blends

Blending natural thermally sensitive biopolymers (collagen, agarose, gelatin and chitosan) with synthetic polymers improves the biocompatibility and bioactive interactions. Hybrid blends have mechanical performance combined with cell-supportive behavior and can be useful for tissue regeneration, injectable cartilage repair and wound sealing [18]. The Thermo-Responsive Polymer Blends: Material Systems, Mechanisms, and Minimally Invasive Applications Table 1

Table 1. Thermo-responsive polymer blends: material systems, mechanisms, and minimally invasive applications.

Polymer blend system	Thermo-responsive mechanism (from CH-9)	Key functional features	Minimally invasive applications
Niam-Based Blends (Niam-PEG, PNIPAAm-chitosan, PNIPAAm-HA, PNIPAAm-PU)	LCST-driven sol-gel transition near physiological temperature	Injectable at room temperature; in situ gelation; tunable LCST; improved biocompatibility	Injectable scaffolds, endoscopic sealants, catheter-delivered drug depots
Ploxamer-Based Blends (Ploxamer-alginate, -chitosan, -gelatin)	Micelle-driven reversible sol-gel transition	Rapid gelation; good rheology; mucoadhesive behavior	Endoscopic hemostasis, intranasal delivery, anti-adhesion barriers
PCL-Containing Blends (PCL-PEG, PCL-urethane, PCL-elastomers)	Thermally activated shape-memory and melting transition near body temperature	Shape recovery; structural stability; biodegradable	Self-expanding stents, occlusion devices, fracture fixation, SMP scaffolds
Natural-Synthetic Hybrid Blends (gelatin, collagen, agarose, chitosan + synthetic polymers)	Temperature-induced gelation combined with bioactive interactions	Enhanced cell compatibility; balanced mechanics; ECM mimicry	Injectable cartilage repair, wound sealing, regenerative scaffolds
Nanocomposite Thermo-Responsive Blends	Enhanced heat transfer and responsiveness via nanoparticles	Faster gelation; improved mechanical strength; multifunctionality	Embolization agents, precision drug delivery, responsive implants
Biofunctionalized Thermo-Responsive Blends	Temperature-triggered deployment with biological targeting	Site-specific adhesion; enhanced therapeutic efficacy	Targeted drug delivery, regenerative therapies
Imaging-Integrated Polymer Blends	Thermo-responsive deployment with imaging visibility	Real-time visualization; procedural accuracy	Endovascular embolization, stent placement, localized therapy

APPLICATIONS IN MINIMALLY INVASIVE MEDICAL PROCEDURES

Injectable Drug Delivery and Localized Therapeutics

Thermo-Responsive polymer blends have revolutionized local drug delivery. They provide an opportunity to deliver the therapeutic depots with precision and minimally invasive tool placement that solidifies after being injected with the functional material. When administered as a liquid, the

polymer transforms into a semi-solid or gel at body temperature thus creating a depot which allows for a sustained release of drugs over a period of days or weeks. The addition of nanoparticles/liposomes enhances the delivery efficiency as well as directs a stimulus-responsive release [19].

These systems have been tested for chemotherapy of solid tumors, antibiotics of orthopedic infections, anti-inflammatories for joint therapy, and growth factors of tissue regeneration [20]. The main benefit is the lack of the need for surgery to achieve the depot position, with an improvement in localization and reduction in systemic toxicity.

Embolization and Vascular Occlusion

Endovascular embolization, typically metal coils or liquid adhesives are typically used. Thermo-responsive blends are a safer and more controllable option. They can pass through microcatheters in liquid form and then shape themselves to a stable plug in a heated state to body temperature. Blends – like PNIPAAm-PEG, PCL-urethane, and poloxamer-based systems – have a high potential as embolic agents as these systems gel predictably and are mechanically stable. Austenitic shape memory polymer plugs fabricated using blends of PCL polymers can expand in aneurysms or vascular malformations for better occlusion results [21].

Tissue Sealing and Hemostasis

Thermo-responsive hydrogels have many applications in endoscopic sealing and hemostats. Poloxamer blends are very popular as they gel fast and apply smoothly. When combined with bio adhesive polymers, they seal gastrointestinal perforations, surgical leaks or bleeding sites much better. Recent work has revealed that the introduction of nanoparticles or peptides enhances coagulation and tissue bonding properties and demonstrates their good use with complex laparoscopic procedures [22].

Orthopedic and Dental Minimally Invasive Interventions

Injectable thermo-responsive polymer blends are increasingly being used in orthopedics and dentistry, where the use of minimally invasive techniques is preferred to limit bone exposure. Scaffolds based on PNIPAAm, gelatin-based blends or soft PCL composites could fill the bone defect and aid in cartilage regeneration and also treat temporomandibular joint disorders [23]. These blends conform to irregular defects, harden or expand in situ and integrate with the host tissue over time.

Endovascular Stents and Devices

Shape-memory polymer blends are also important for catheter delivered stents and occlusion devices. PCL-based SMAe can be compressed into temporary shape for insertion through narrow catheters – when it reaches body temperature, it will re-return to functional shape. Elastomers are added to increase the toughness whereas radiopaque fillings help in imaging guidance [24]. These polymeric stents may be degradable and are less chronic inflammatory compared to metal stents.

Adhesion Prevention in Minimally Invasive Surgery

Post operative adhesions are still a problem with laparoscopic surgery. Thermo-responsive blends to form temporary barriers, body temperature can provide protection to surgical sites. Poloxamer-hyaluronic acid, PEG-polyester, and gelatin-based blends have been tested for the ability to produce hydrogels for resistance to adhesion for several weeks before slowly breaking down [25].

Injectable Tissue Engineering and Regenerative Medicine

Thermo-responsive polymer blends are increasingly used as injectable scaffolds for tissue engineering and regenerative medicine. These materials can be delivered through minimally invasive techniques and undergo in situ gelation at body temperature, providing a three-dimensional matrix for cell attachment, proliferation, and tissue repair [26]. Blends containing PNIPAAm, PEG, PCL, gelatin, or chitosan support the controlled delivery of cells and bioactive molecules while gradually degrading as new tissue forms. Their excellent biocompatibility and ability to conform to irregular defects make them promising candidates for cartilage regeneration, soft tissue repair, skin wound healing, and bone tissue engineering in minimally invasive clinical procedures.

ADVANCES IN BLEND ENGINEERING

Nanocomposite Thermo-Responsive Systems

Nanocomposites are a breakthrough in polymer blends technology. The use of nanoparticles – such as silica, graphene, gold, or clay – helps to increase mechanical strength, thermal stability, and responsiveness. For example, graphene oxide incorporated in PNIPAAm blends accelerated the heat transfer, which results in accelerated gelation or shape recovery during the procedures [27]. Nanoparticles also offer other functions such as magnetic control or increased drug loading.

Biodegradability and Controlled Degradation

One of the challenges for minimally invasive materials is to allow safe degradation over a clinically-appropriate time. Researchers are using fast degrading hydrogels with slower degrading polyesters in an attempt to tune the degradation profiles they have. Blends of PCL-tablet PLA, PEG-polyester copolymers, urethane-based SMPs enable adjustable rates to meet application requirements, be it temporary embolization or long-term tissue regeneration [28].

Biofunctionalization for Targeted Procedures

Recent attempts involve decorating thermo-obvious (-responsive) blends with peptides, growth factors or antibodies to promote site specific interactions. Integrin-binding peptides promote cell adhesion in injectable scaffolds and ligands against cancer target polymer depots to malignant tissue. Blending biofunctionalized polymers is a way to provide a powerful platform for targeted, minimally invasive therapy with improved outcomes [29].

Imaging-Integrated Blends

Thermo-responsive blends are increasingly comprised of materials that can be imaged. The use of radiopaque nanofillers allows placing polymers to be visualized by surgeons in real time. This integration is crucial for vascular occlusion, stent deployment and local drug delivery, for which precision is important [30].

Mechanical Property Optimization

Optimizing the mechanical properties of thermo-responsive polymer blends is essential for minimally invasive medical procedures. By blending flexible and rigid polymers, researchers can improve elasticity, toughness, and compressive strength while maintaining temperature responsiveness. These optimized blends provide better structural stability for injectable hydrogels, tissue scaffolds, and shape-memory devices used in clinical applications [31].

Sterilization and Clinical Translation

Successful clinical application requires thermo-responsive polymer blends to retain their functional properties after sterilization. Current studies focus on developing blend formulations that remain stable following gamma irradiation, ethylene oxide, or steam sterilization without affecting their thermo-responsive behavior or biocompatibility. These advances are expected to facilitate regulatory approval and wider clinical adoption of minimally invasive polymer-based devices [32].

CHALLENGES AND FUTURE DIRECTIONS

Although thermo-responsive polymer blends are very promising, there are challenges. Precisely, reproducible responses at body temperature are critical; temperature variations even a few degrees can have an impact on gelation or shape recovery. Balancing mechanical strength with injectability is also difficult: stiffer gels have increased stability but are harder to inject through small catheters.

Biocompatibility and long-term interactions with the tissues are key issues. Some blends give out acidic byproducts or cause inflammations and, therefore, sophisticated purification, chemical modification, or the addition of natural polymers are required. Regulatory approval is also difficult since responsive biomaterials require extensive safety testing.

Future research should focus on multi-responsive systems, which include thermo-responsiveness with one or more additional triggers such as pH, enzyme or magnetic. Artificial intelligence in predictive material design can accelerate discovery of means to the optimal mixtures. 3D printing using thermo-responsive inks is another promise, which can become the basis for personalized implants deployable by minimally invasive means.

CONCLUSION

Thermo-responsive polymer blends are a great leap for smart biomaterials for minimally-invasive procedures. Their capacity to undergo phase, shape or mechanical changes at body temperature enables intervention with precision and on a targeted patient-friendly basis. Indexing composition, synthetic and natural combinations and nanofillers or bioactive, researchers can rationally design versatile systems for embolization, drug delivery, sealing, scaffolding and stent deployment. These materials have advantages over conventional devices because they provide minimally invasive delivery methods, design adaptability inside the body and have reduced postoperative complications. The continued progress made in polymer chemistry, nanotechnology, and functionalizing organisms indicates that even more tailored thermos-favorable systems with clinical significance are to be expected. As the research continues improvements in safety, predictability, imaging compatibility, and biodegradability will increase their therapeutic potential. Ultimately, thermo-responsive polymer blends will become key to next generation medical classes and regeneration methods to enhance patient outcomes and reduce surgical trauma.

REFERENCES

1. Behera A, Nayak AK, Mohapatra RK, Rabaan AA, editors. Smart micro- and nanomaterials for pharmaceutical applications. CRC Press; 2024 Aug 27.
2. Zhang H, Zhou J. Bio-based hydrogels in biomedical applications. In: Green by design: Harnessing the power of bio-based polymers at interfaces. Bristol, UK: IOP Publishing; 2024 Dec 1. p. 4–1.
3. Neumann M, Di Marco G, Iudin D, Viola M, van Nostrum CF, van Ravensteijn BG, et al. Stimuli-responsive hydrogels: The dynamic smart biomaterials of tomorrow. *Macromolecules*. 2023;56(21):8377–92.
4. Gao Q, Lee JS, Kim BS, Gao G. Three-dimensional printing of smart constructs using stimuli-responsive biomaterials: A future direction of precision medicine. *Int J Bioprint*. 2023;9(1):638.
5. Jeewantha LH, Islam MM, Epaarachchi JA. Development of smart materials for invasive medical applications using shape memory polymers. In: 6th International Conference on Mechanical, Industrial and Energy Engineering (ICMIEE 2020). University of Southern Queensland; 2020.
6. Chatterjee S, Hui PC, Kan CW. Thermoresponsive hydrogels and their biomedical applications: Special insight into their applications in textile based transdermal therapy. *Polymers (Basel)*. 2018;10(5):480.
7. Liu H, Prachyathipsakul T, Koyasseril-Yehiya TM, Le SP, Thayumanavan S. Molecular bases for temperature sensitivity in supramolecular assemblies and their applications as thermoresponsive soft materials. *Mater Horiz*. 2022;9(1):164–93.
8. Hu X, Wang J, Yang S, Deng J, Feng W, Wu H, et al. Evaluation of the 3D printable temperature-responsive shape-memory PLTG terpolymers for minimally invasive surgery. *Bio-Des Manuf*. 2025;8(5):709–23.
9. Lv T, Chen Y, Li N, Liao X, Heng Y, Guo Y, et al. A comprehensive review of thermosensitive hydrogels: Mechanism, optimization strategies, and applications. *Gels*. 2025;11(7):544.
10. Prem Kumar C, Sivanagaraju N, Loknath D, Mallikarjun Rao GN, Vakkalagadda MR. Shape memory polymers, blends, and composites: Processing, properties, and applications. *Polym Plast Technol Mater*. 2025;64(9):1253–81.
11. Quan X, Cui K, Huang S, Jiang G, Miao Z. Intelligent UCST-responsive hydrogels with reversible swelling for enhanced wellbore stability. *Colloids Surf A Physicochem Eng Asp*. 2025 Nov 20;725:137709.

12. Park J, Guan W, Yu G. Smart hydrogels for sustainable agriculture. *EcoMat*. 2025 Apr;7(4):e70011.
13. Ayaz U, Zaman M, Hameed H, Naeem S, Noor Khan I, Ahsan Waqar M, et al. DMARDs incorporated injectable hydrogels in cartilage tissue regeneration: A review. *Polym Plast Technol Mater*. 2024;63(14):1843–60.
14. Gheysoori P, Paydayesh A, Jafari M, Peidayesh H. Thermoresponsive nanocomposite hydrogels based on gelatin/poly(N-isopropylacrylamide) (PNIPAM) for controlled drug delivery. *Eur Polym J*. 2023 Mar 15;186:111846.
15. Russo E, Villa C. Poloxamer hydrogels for biomedical applications. *Pharmaceutics*. 2019;11(12):671.
16. Zhang K, Xue K, Loh XJ. Thermo-responsive hydrogels: From recent progress to biomedical applications. *Gels*. 2021;7(3):77.
17. Dhote NS, Patel RD, Kuwar U, Agrawal M, Alexander A, Jain P, et al. Application of thermoresponsive smart polymers based in situ gel as a novel carrier for tumor targeting. *Curr Cancer Drug Targets*. 2024;24(4):375–96.
18. Hsieh CH, Mohd Razali NA, Lin WC, Yu ZW, Istiqomah D, Kotsuchibashi Y, et al. Development of thermo-responsive polycaprolactone-polydimethylsiloxane shrinkable nanofibre mesh. *Nanomaterials (Basel)*. 2020;10(7):1427.
19. Oliveira MB, Mano JF. Natural-based and stimuli-responsive polymers for tissue engineering and regenerative medicine. In: *Polymers in regenerative medicine: Biomedical applications from nano- to macro-structures*. 2014 Oct 24. p. 49–90.
20. Ebrahimnia M, Alavi S, Vaezi H, Iradmousa MK, Haeri A. Exploring the vast potentials and probable limitations of novel and nanostructured implantable drug delivery systems for cancer treatment. *EXCLI J*. 2024 Feb 1;23:143.
21. Li L, Yang WW, Xu DG. Stimuli-responsive nanoscale drug delivery systems for cancer therapy. *J Drug Target*. 2019 Apr 21;27(4):423–433.
22. Liu Y, Liu J, Zheng C, Ma Z. Recent advances in embolic agents for transarterial chemoembolization of hepatocellular carcinoma. *Adv Healthc Mater*. 2026 Mar;15(10):e02566.
23. Ding A, Tang F, Alsberg E. The emerging 4D printing of shape-memory thermomorphs for self-adaptive biomedical implants. *Adv Funct Mater*. 2025;35(28):2418348. doi: [10.1002/adfm.202418348](https://doi.org/10.1002/adfm.202418348).
24. Askari E, Seyfoori A, Amereh M, Gharaie SS, Ghazali HS, Ghazali ZS, et al. Stimuli-responsive hydrogels for local post-surgical drug delivery. *Gels*. 2020;6(2):14.
25. Tian ML, Zhou JF, Qi X, Shen R. Thermo-sensitive hydrogel and their biomedical applications. In: *IOP Conference Series: Earth and Environmental Science*. 2021;714(3):032062.
26. Huang L, Abdalla AM, Xiao L, Yang G. Biopolymer-based microcarriers for three-dimensional cell culture and engineered tissue formation. *Int J Mol Sci*. 2020;21(5):1895.
27. Zhang Y, Xu H, Wang J, Fan X, Tian F, Wang Z, et al. Incorporation of synthetic water-soluble curcumin polymeric drug within calcium phosphate cements for bone defect repairing. *Mater Today Bio*. 2023 Jun 1;20:100630.
28. Fazel Anvari-Yazdi A, Badea I, Chen X. Biomaterials in postoperative adhesion barriers and uterine tissue engineering. *Gels*. 2025;11(6):441.
29. Sarwan T, Kumar P, Choonara YE, Pillay V. Hybrid thermo-responsive polymer systems and their biomedical applications. *Front Mater*. 2020 Mar 31;7:73.
30. Zheng J, Zhu C, Xu X, Wang X, Fu J. Supramolecular assemblies of multifunctional microgels for biomedical applications. *J Mater Chem B*. 2023;11(27):6265–89.
31. Beilharz S, Debnath MK, Vinella D, Shoffstall AJ, Karayilan M. Advances in injectable polymeric biomaterials and their contemporary medical practices. *ACS Appl Bio Mater*. 2024;7(12):8076–101.
32. Li T, Chen L, Yuan Y, Shi R. The current status, prospects, and challenges of shape memory polymers application in bone tissue engineering. *Polymers (Basel)*. 2023;15(3):556.