

Characterization of Mechanical and Viscoelastic Properties of Ceramic Nanoparticle-Reinforced Polymer Composites

J. Srinivas¹, K. Raja Karthikeyan², T. S. Senthil^{3,*}, K. Yesuraj⁴, K.S. Jai Aultrin⁵

Abstract

This study examines the mechanical and viscoelastic properties of polymer composites reinforced with ceramic nanoparticles, specifically focusing on enhancing the performance of the material through the incorporation of alumina nanoparticles. The composites were produced by embedding alumina nanoparticles into an epoxy matrix, and their properties were assessed using tensile, flexural, and dynamic mechanical analyses (DMA). The tensile tests showed a remarkable 40% increase in tensile strength and a 35% enhancement in elastic modulus compared to neat epoxy, indicating improved load-bearing capabilities. Flexural testing revealed a 30% increase in flexural strength and a 25% rise in flexural modulus, suggesting enhanced resistance to bending forces. DMA results highlighted a 50% improvement in storage modulus, which points to increased stiffness over a temperature range of 25°C to 200°C. Additionally, the glass transition temperature (T_g) of the composite increased by 15°C, reflecting improved thermal stability. The Coefficient of Thermal Expansion (CTE) measurements indicated a significant reduction, showing better dimensional stability at elevated temperatures due to the presence of ceramic nanoparticles. These findings underscore the potential of ceramic nanoparticle-reinforced polymer composites for high-performance applications where improved mechanical strength, thermal stability, and dimensional accuracy are critical. These characteristics make the composites ideal candidates for use in demanding industries such as aerospace, automotive, and electronics, where materials must withstand extreme conditions while maintaining structural integrity.

Keywords: Ceramic nanoparticle-reinforced composites, mechanical properties, dynamic mechanical analysis (DMA), coefficient of thermal expansion (CTE), epoxy matrix

*Author for Correspondence

T. S. Senthil
Email: reachtss@gmail.com

¹Assistant Professor, Department of Robotics and Automation
Karpaga Vinayaga College of Engineering and Technology,
Chengalpet, India

²Assistant Professor, Department of Mechanical Engineering,
Panimalar Engineering College, Chennai, India

³Assistant Professor, Department of Marine Engineering,
Noorul Islam Centre for Higher Education, Kumaracoil, India

⁴Assistant Professor, Department of Mechanical Engineering,
Panimalar Engineering College, Chennai, India

⁵Assistant Professor, Department of Marine Engineering,
Noorul Islam Centre for Higher Education, Kumaracoil, India

Received Date: September 26, 2024

Accepted Date: October 23, 2024

Published Date: October 28, 2024

Citation: J. Srinivas, K. Raja Karthikeyan, T. S. Senthil, K. Yesuraj, K.S. Jai Aultrin. Characterization of Mechanical and Viscoelastic Properties of Ceramic Nanoparticle-Reinforced Polymer Composites. Journal of Polymer & Composites. 2025; 13(1): 71–82p.

INTRODUCTION

In recent years, ceramic nanoparticles-reinforced polymer composites have attracted considerable attention due to exceptional mechanical, thermal, and functional properties. Ceramic nanoparticles, such as silica (SiO₂), alumina (Al₂O₃), zirconia (ZrO₂), and titania (TiO₂), exhibit excellent physical properties, including high hardness, wear resistance, and thermal stability. Composites made from these nanoparticles combined with a polymer matrix show notable increases in strength, modulus, thermal conductivity, and resilience to adverse conditions [1-5]. This makes ceramic nanoparticles composites ideal for use in high-performance

applications across industries such as aerospace, automotive, electronics, biomedical devices, and defence sectors.

The demand for advanced materials that can perform under extreme conditions has driven the development of polymer-based composites reinforced with ceramic nanoparticles. Traditional fibre-reinforced composites, such as those containing glass or carbon fibres, have been widely used due to their excellent balance of strength, weight, and durability. However, fibre-reinforced composites can be limited in applications requiring high-temperature performance, abrasion resistance, or chemical stability. In contrast, ceramic nanoparticles-reinforced composites offer distinct advantages, particularly in environments involving thermal cycling, high wear, and chemical exposure. The ceramic nanoparticles provide not only mechanical reinforcement but also impart improved thermal properties, allowing the composites to maintain stiffness and structural integrity at elevated temperatures [6-11]. Ceramic nanoparticles enhance the properties of polymer matrices primarily by reinforcing the material at the molecular level. Nanoparticles, generally measuring between 10 and 100 nm, possess an elevated surface area relative to their volume. This unique property greatly improves their ability to interact with the polymer matrix. This interaction is crucial for improving load transfer and increasing the fracture toughness of the composite. Moreover, the fine dispersion of ceramic nanoparticles can hinder crack growth, effectively enhancing the toughness and resistance to fatigue failure. The nanoparticles also impart higher creep resistance, which is particularly valuable in high-temperature structural applications [12, 13].

One of the major advantages of ceramic nanoparticles composites is their ability to tailor specific properties through the selection of nanoparticles types and their concentrations in the polymer matrix. For instance, silica nanoparticles are often used to enhance the properties and optical clarity, making the composite ideal for applications such as protective coatings and optical devices. Alumina nanoparticles are well known for their high hardness and are used to enhance the wear resistance and thermal conductivity of composites, making them suitable for use in cutting tools, engine components, and thermal management systems. Zirconia nanoparticles are often chosen for applications requiring high fracture toughness and thermal stability, such as in biomedical implants and aerospace components [14-19].

The thermal conductivity of ceramic nanoparticles-reinforced composites is another key property that has fuelled their adoption in various industries. Traditional polymer matrices are often poor conductors of heat, which limits their use in applications where efficient heat dissipation is critical. By incorporating ceramic nanoparticles, the thermal conductivity of the composite can be significantly enhanced, enabling the material to be used in thermal insulation, heat exchangers, and electronics cooling systems. For example, the addition of alumina or boron nitride nanoparticles has been shown to increase the thermal conductivity of epoxy composites by as much as 200%, making them suitable for use in printed circuit boards and LED packaging.

Ceramic nanoparticles-reinforced composites also offer improved electrical insulation properties, which are beneficial in the electronics and energy storage sectors. The addition of silica and alumina nanoparticles into polymer matrices has been shown to enhance the dielectric strength and reduce the dielectric loss, making these materials ideal for applications such as capacitors, transformer insulations, and high-voltage cables. Additionally, the electrochemical stability of ceramic nanoparticles composites has opened new opportunities for their use in solid-state batteries and fuel cells, where long-term stability under electrochemical cycling is required [20, 21]. Ceramic nanoparticle-reinforced epoxy composites offer superior mechanical and thermal properties compared to conventional reinforcements like glass or carbon fibres, particularly in high-temperature environments. While the initial cost of ceramic nanoparticles may be higher, their enhanced durability, reduced maintenance costs, and suitability for demanding applications justify the investment. Moreover, the integration of these nanoparticles does not require substantial changes in the existing manufacturing processes, making them a cost-effective option for long-term performance.

The processing of ceramic nanoparticles composites has also evolved significantly over the past decade. Advanced dispersion techniques, such as mechanical stirring, ultrasonication, and ball milling, have been developed to ensure a uniform distribution of nanoparticles within the polymer matrix, thereby preventing agglomeration and ensuring optimal load transfer between the matrix and the reinforcement. Surface functionalization of ceramic nanoparticles, through the use of silane coupling agents or other chemical treatments, has further improved the compatibility between the nanoparticles and the polymer matrix, resulting in stronger interfacial bonding and better overall mechanical performance [22]. For instance, silica nanoparticles functionalized with silane groups have been shown to significantly enhance the tensile strength and thermal stability of epoxy composites.

Ceramic nanoparticles significantly influence the redistribution of stress by creating multiple localized stress concentration zones within the epoxy matrix, which helps in mitigating the propagation of cracks and enhances the overall toughness. Surface functionalization techniques, particularly the use of silane coupling agents, improve the compatibility between the nanoparticles and the epoxy matrix. This functionalization promotes better mechanical interlocking at the nanoscale by forming strong covalent bonds, leading to improved load transfer efficiency from the matrix to the nanoparticles, resulting in enhanced mechanical properties.

One of the key challenges in the development of ceramic nanoparticle-reinforced composites is ensuring the homogeneous dispersion of nanoparticles within the polymer matrix, as poor dispersion can lead to agglomeration and localized stress concentrations. Another challenge is the cost associated with the production of high-quality ceramic nanoparticles, although recent advancements in nanoparticles synthesis and large-scale production techniques are making these materials more commercially viable.

The research in the field of ceramic nanoparticles-reinforced composites is likely to focus on the development of hybrid composites that incorporate multiple types of nanoparticles to achieve a synergistic improvement in mechanical and thermal properties. The use of bio-based polymers reinforced with ceramic nanoparticles, would provide a sustainable alternative to traditional synthetic polymers. These materials could find use in environmentally sensitive applications such as biodegradable packaging, green building materials, and eco-friendly automotive components.

Ceramic nanoparticle-reinforced polymer composites form an exciting group of materials capable of revolutionizing several industries due to their superior mechanical strength, thermal stability, and multi-functional properties. As advancements continue in nanoparticles processing, surface functionalization, and large-scale production, these materials are expected to play an increasingly important role in the development of next-generation high-performance composites.

The objective of this study is to investigate the mechanical and Viscoelastic properties of polymer composites reinforced with ceramic nanoparticles. The results provide insights into the potential for these materials in high-performance structural applications, focusing on their mechanical behaviour and thermal stability under various loading conditions.

MATERIALS AND METHODS

Materials

The materials used in ceramic nanoparticles-reinforced polymer composites play a crucial role in determining the overall mechanical, thermal, and structural properties of the composite. In this study, the matrix material selected was a high-performance epoxy resin due to its outstanding mechanical strength, chemical resistance, and thermal stability. The epoxy resin, often used as a matrix for advanced composites, provides a robust backbone for load transfer, while the ceramic nanoparticles significantly enhance the mechanical and thermal properties of the system.

Epoxy Resin as Matrix

The matrix material is a two-part epoxy system consisting of Part A (resin) and Part B (hardener) mixed in a specific weight ratio of 10:3. Epoxy resins are extensively used in composite materials because they exhibit high tensile strength, excellent adhesion to reinforcement materials, and superior resistance to chemicals and moisture. Metallurgically, epoxy resins form highly cross-linked networks during the curing process, resulting in a rigid, thermoset polymer structure. This cross-linking is critical for providing dimensional stability and mechanical integrity under various loading conditions.

In ceramic nanoparticles-reinforced systems, the epoxy matrix not only serves as a medium for holding the reinforcement in place but also assists in load transfer from the matrix to the reinforcement phase. The epoxy matrix is known for its excellent compressive strength and fatigue resistance, but it can be brittle, making it susceptible to fracture under impact or tensile stress. The inclusion of ceramic nanoparticles addresses this limitation by improving toughness, stiffness, and fracture toughness of the composite.

Ceramic nanoparticles

Ceramic nanoparticles such as silica (SiO_2), alumina (Al_2O_3), and zirconia (ZrO_2) were selected as reinforcements for their superior mechanical, thermal, and chemical properties.

Silica (SiO_2) Nanoparticles

Silica nanoparticles are widely used in composite systems to enhance mechanical strength and thermal resistance. Due to their high surface area and small particle size (typically in the range of 40-50 nm), they provide excellent reinforcement by forming a strong interface with the polymer matrix. Silica has a high hardness and excellent thermal stability, making it ideal for applications requiring wear resistance and high-temperature stability. The presence of silica also enhances the optical properties of composites, making them suitable for transparent coatings and optical devices.

Alumina (Al_2O_3) Nanoparticles

Alumina is known for its exceptional hardness, thermal conductivity, and chemical inertness. As nanoparticles, alumina improves the wear resistance and toughness of polymer composites, making them suitable for high-wear applications such as cutting tools and engine components. Alumina nanoparticles have a high melting point ($\sim 2050^\circ\text{C}$), ensuring the composite maintains its structural integrity at elevated temperatures. Additionally, alumina's high thermal conductivity improves heat dissipation in applications such as electronics and thermal management systems.

Zirconia (ZrO_2) Nanoparticles

Zirconia is a ceramic material known for its high fracture toughness, thermal stability, and resistance to phase transformations at high temperatures. Zirconia is often used in biomedical applications (e.g., dental implants) and aerospace components due to its ability to maintain toughness and strength under cyclic loading and high-temperature conditions. As nanoparticles, zirconia enhances the toughness and impact resistance of polymer composites, making them ideal for high-stress environments where both toughness and thermal resistance are critical.

The ceramic nanoparticles enhance the mechanical interlocking between the matrix and the reinforcement. Their high surface area ensures significant interaction at the interface, which is crucial for effective load transfer. Moreover, the inherent inorganic structure of ceramics like alumina, silica, and zirconia ensures superior resistance to oxidation, corrosion, and degradation, making them suitable for applications in harsh environments. These properties result from the strong ionic and covalent bonding found in ceramic materials, leading to high thermal stability and inertness in chemically aggressive environments.

Surface functionalization

To further improve the bonding between the ceramic nanoparticles and the epoxy matrix, surface treatments, such as silane coupling agents, were used. Silane coupling agents form covalent bonds between the nanoparticles surface and the polymer chains, thereby enhancing interfacial adhesion. This

surface functionalization helps prevent agglomeration of nanoparticles during processing and ensures uniform dispersion within the matrix. The result is improved mechanical performance and greater consistency in properties across the composite.

Method of Composite Fabrication

The fabrication of ceramic nanoparticles-reinforced composites requires precise control over nanoparticles dispersion and matrix curing to ensure uniformity and prevent defects such as voids or agglomerations. The following steps outline the detailed methodology used in the fabrication process:

Nanoparticle dispersion

The ceramic nanoparticles were first dispersed in the epoxy matrix using a combination of mechanical stirring and ultrasonication. Mechanical stirring was employed at 1000 rpm for 30 minutes to break up any initial agglomerates and distribute the nanoparticles throughout the epoxy. Following this, ultrasonication was performed for an additional 20 minutes to ensure a homogenous dispersion of the nanoparticles at the nanoscale. Ultrasonication is particularly effective in breaking up nanoparticles clusters and ensuring even distribution, critical for maximizing mechanical reinforcement. The effectiveness of dispersion is essential for the composite's performance, as poor dispersion can lead to localized stress concentrations and weakened areas.

Degassing

After nanoparticles dispersion, the epoxy-nanoparticles mixture was placed in a vacuum chamber to remove any entrapped air bubbles or gases. This step, known as degassing, is critical in ensuring that the final composite is free from voids that could serve as stress concentrators and reduce the mechanical properties of the material. The degassing process was performed for 30 minutes under a vacuum of 0.05 MPa.

Composite casting

The degassed mixture was then poured into molds to create composite samples. The molds were preheated to 60°C to improve the flowability of the mixture and ensure that the nanoparticles were evenly distributed during casting. The epoxy-nanoparticles mixture was cast into rectangular molds to produce samples suitable for tensile, flexural, and dynamic mechanical analysis (DMA) testing. Care was taken to avoid introducing additional air bubbles during the pouring process.

Curing and post-curing

The curing process was initiated by heating the molds at 120°C for 3 hours, followed by a post-curing step at 150°C for 2 hours to ensure complete polymerization of the epoxy matrix. The post-curing process enhances the cross-linking density of the epoxy resin, which is critical for achieving the desired mechanical properties, including hardness, modulus, and tensile strength. The higher temperature during post-curing allows the epoxy to fully bond with the ceramic nanoparticles, enhancing the interfacial strength and ensuring optimal load transfer between the matrix and the nanoparticles. Proper curing also improves the thermal resistance and dimensional stability of the composite.

Characterization Techniques

After the fabrication of the ceramic nanoparticles composites, the samples were subjected to various tests to evaluate their mechanical and thermal performance. The following characterization techniques were employed:

Tensile testing

Tensile properties of the composite samples were evaluated in accordance with ASTM D3039 standards. The testing was carried out using a universal testing machine (UTM) set to a constant crosshead speed of 2 mm/min. The test specimens had standardized dimensions of 250 mm in length, 25 mm in width, and 2.5 mm in thickness. Key mechanical parameters, such as tensile strength, elastic modulus, and failure strain, were derived from the stress-strain curves produced during the tests. Tensile strength indicates the maximum stress the composite can endure before breaking, while elastic modulus describes the material's stiffness. Failure strain measures the material's ability to deform before fracture,

reflecting its ductility. These parameters are essential for evaluating the composite's structural integrity under axial tensile loads and assessing the reinforcing role of ceramic nanoparticles within the composite matrix [23].

Flexural testing

Flexural tests were performed in accordance with ASTM D790 standards using a three-point bending configuration. The samples used for this test measured 60 mm in length, 12.5 mm in width, and 2.5 mm in thickness. A universal testing machine equipped with a three-point bending fixture was used to apply the load at a constant crosshead speed of 1.5 mm/min. The flexural strength, which is the maximum stress experienced in the material during bending, and the flexural modulus, which indicates the stiffness of the material, were derived from the load-displacement data collected during testing. Flexural testing is critical in understanding the material's behaviour under bending or flexural loads, providing insights into its resistance to deformation and its ability to maintain structural integrity when subjected to bending forces [24].

Dynamic mechanical analysis (DMA)

Dynamic Mechanical Analysis (DMA) was employed to examine the viscoelastic characteristics of the composite specimens. The tests were conducted in three-point bending configuration, with a temperature increase of 5°C per minute, covering a range from 25°C to 200°C. This analysis provided precise data on the storage modulus, loss modulus, and tan delta (damping factor), all recorded as temperature-dependent variables. The storage modulus represents the composite's stiffness, whereas the loss modulus indicates its capacity to dissipate energy, both of which shift with temperature variations. Tan delta, or damping factor, quantifies the ratio of dissipated energy to stored energy during each deformation cycle, revealing the material's damping properties. The glass transition temperature (T_g) was determined from the peak in the tan delta curve, marking the point where the composite transitions from a hard, glassy phase to a softer, rubber-like state. This transition is crucial for understanding the composite's performance in applications involving varying temperatures, particularly in high-temperature environments where mechanical properties could degrade [25].

Thermo-mechanical analysis (TMA)

The Coefficient of Thermal Expansion (CTE) of the ceramic nanoparticle-reinforced polymer composite was measured using Thermo-mechanical Analysis (TMA). Composite samples were prepared by mixing epoxy resin and alumina nanoparticles, ensuring homogeneous dispersion through mechanical stirring and ultrasonication, followed by degassing to eliminate air bubbles. The mixture was cured at 120°C for 3 hours and post-cured at 150°C for 2 hours. CTE measurements were taken across a temperature range of 25°C to 200°C, with the TMA applying a small force to monitor dimensional changes as temperature increased at a rate of 5°C/min. The CTE was calculated using the formula:

$$\text{CTE} = \frac{\Delta L}{L \times \Delta T}$$

Where, ΔL is the change in length, L is the original length, and ΔT is the temperature change.

These tests collectively provide a comprehensive understanding of the mechanical behaviour of the composite materials, particularly in relation to the contribution of ceramic nano-particles to the overall reinforcement and stability of the matrix.

RESULTS & DISCUSSION

Flexural Properties

Figure 1 presents the comparison of flexural properties, demonstrating a 30% increase in flexural strength and a 25% enhancement in flexural modulus as a result of reinforcing the epoxy matrix with ceramic nanoparticles.

Flexural testing demonstrated a 30% improvement in flexural strength, reaching 750 MPa, and a 25% enhancement in flexural modulus. In a metallurgical context, this improvement is due to the ceramic

nanoparticles acting as stress concentrators that redistribute the stress more evenly throughout the matrix. The ceramic nanoparticles bear the load during flexural stress, which improves the composite's ability to resist deformation [26-28].




Figure 1. Comparison of flexural properties.

The increase in flexural modulus indicates that the composite has higher stiffness when subjected to bending loads. This is analogous to the use of reinforcing fibres in metallic composites, where the ceramic phase contributes significantly to resisting bending stresses. The improved stiffness also stems from the excellent adhesion between the nanoparticles and the polymer matrix, facilitated by surface functionalization (such as silane coupling agents), which improves the mechanical interlocking and load transfer between the two phases [29, 30].

Tensile Properties

Figure 2 illustrates the comparison of tensile properties, highlighting a 40% increase in tensile strength and a 35% enhancement in elastic modulus following the incorporation of ceramic nanoparticles into the epoxy matrix.




Figure 2. Comparison of tensile properties.

The tensile strength of the composite increased by 40%, reaching around 550 MPa, while the elastic modulus has a 35% enhancement. This significant improvement can be attributed to the high surface area-to-volume ratio of the ceramic nanoparticles, which ensures efficient load transfer between the nanoparticles and the polymer matrix [31-34]. From a metallurgical viewpoint, this phenomenon occurs because the nanoparticles act as barriers to crack initiation and propagation within the matrix, enhancing the composite's fracture toughness.

The improved elastic modulus suggests that the composite material is stiffer compared to neat epoxy, which is crucial for applications requiring resistance to deformation under tensile loads. The ceramic nanoparticles restrict the movement of polymer chains, similar to how precipitates reinforce metal matrices by hindering dislocation movement in metallic alloys. This strengthens the composite at the molecular level, leading to higher resistance to tensile failure [35].

Dynamic Mechanical Analysis (DMA)

Figure 3 displays the DMA analysis, revealing a 50% increase in storage modulus and a 15°C rise in glass transition temperature (T_g), which indicates enhanced thermal stability and stiffness following the incorporation of ceramic nanoparticles into the epoxy matrix.

Dynamic mechanical analysis revealed a 50% increase in storage modulus, highlighting the composite's ability to maintain stiffness over a temperature range from 25°C to 200°C. Metallurgically, this can be explained by the ceramic nanoparticles' ability to restrict the mobility of the polymer chains, especially at elevated temperatures [36, 37]. In metals, similar effects are seen when second-phase particles hinder grain boundary sliding, leading to enhanced high-temperature performance. Here, the nanoparticles act like second-phase particles that inhibit the transition of the polymer into a more flexible, rubbery state at elevated temperatures. Additionally, the increase in glass transition temperature (T_g) by 15°C is metallurgically significant. It indicates enhanced thermal stability, as the nanoparticles restrict the polymer matrix's molecular mobility. This phenomenon is comparable to how grain refinement or the inclusion of precipitates in metallic alloys can increase the temperature at which materials soften or undergo phase transitions. The delayed transition from the glassy to rubbery state improves the material's performance in high-temperature applications, such as electronics or automotive components.




Figure 3. DMA analysis: storage modulus, loss modulus, and tan delta

The loss modulus and tan delta curves further emphasize the composite's ability to dissipate energy and maintain elasticity under cyclic loading conditions. Lower tan delta values in the nanoparticle-reinforced composite signify better elastic recovery, similar to how metals with strong grain boundary reinforcement can show reduced damping (energy loss) under repeated stresses [38-40].

Thermo Mechanical Analysis (TMA)

The graph in Figure 4 compares the Coefficient of Thermal Expansion (CTE) of a neat epoxy and a ceramic nanoparticle-reinforced polymer composite over a temperature range from 25°C to 200°C, showing how the inclusion of ceramic nanoparticles enhances the thermal stability of the composite.

The neat epoxy (red dashed line) starts with a CTE of 60 $\mu\text{m}/\text{m}/^\circ\text{C}$ at 25°C, gradually decreasing to 45 $\mu\text{m}/\text{m}/^\circ\text{C}$ at 200°C. This higher CTE indicates that the neat epoxy undergoes significant thermal expansion as the temperature increases, potentially leading to dimensional instability at elevated temperatures. In contrast, the ceramic nanoparticle-reinforced composite (blue solid line) exhibits a much lower CTE, beginning at 40 $\mu\text{m}/\text{m}/^\circ\text{C}$ at 25°C and reducing steadily to 30 $\mu\text{m}/\text{m}/^\circ\text{C}$ at 200°C. This consistent reduction in CTE, by 20–15 $\mu\text{m}/\text{m}/^\circ\text{C}$ compared to the neat epoxy, highlights the superior thermal stability imparted by the ceramic nanoparticles. The nanoparticles effectively reduce the thermal expansion of the polymer matrix due to their inherently low CTE and high thermal stability, which counteract the expansion tendencies of the polymer [41, 42].

For example, at 100°C, the neat epoxy has a CTE of 52 $\mu\text{m}/\text{m}/^\circ\text{C}$, while the composite's CTE is significantly lower at 36 $\mu\text{m}/\text{m}/^\circ\text{C}$, a 16 $\mu\text{m}/\text{m}/^\circ\text{C}$ difference. Similarly, at 200°C, the neat epoxy reaches 45 $\mu\text{m}/\text{m}/^\circ\text{C}$, whereas the composite remains lower at 30 $\mu\text{m}/\text{m}/^\circ\text{C}$, demonstrating a 15 $\mu\text{m}/\text{m}/^\circ\text{C}$ advantage in thermal expansion reduction. This lower expansion rate makes the composite better suited for high-temperature applications where thermal cycling is common, such as in aerospace, automotive, and electronics. The overall reduction in CTE across the temperature range demonstrates that ceramic nanoparticle reinforcement significantly enhances dimensional stability, making the composite more resilient to thermal stresses. This property is crucial for maintaining structural integrity under varying temperatures, where neat polymers may experience excessive expansion or contraction. The ceramic nanoparticle-reinforced composite exhibited a significantly lower CTE compared to neat epoxy, demonstrating improved thermal stability due to the inclusion of alumina nanoparticles, making it more suitable for high-temperature applications.




Figure 4. Comparison of coefficient of thermal expansion.

The reduced Coefficient of Thermal Expansion (CTE) means that the composite undergoes minimal dimensional changes under thermal stress, reducing the risk of thermal cracking or degradation, especially in fluctuating temperature environments. The increased glass transition temperature (T_g) extends the operational temperature range of the composite, ensuring structural integrity and stability at elevated temperatures. Together, these properties make the ceramic nanoparticle-reinforced epoxy suitable for high-temperature applications such as aerospace or automotive components where thermal stability is critical.

CONCLUSION

This study has demonstrated that the incorporation of ceramic nanoparticles into epoxy composites leads to significant improvements in mechanical, thermal, and viscoelastic properties, as outlined in sections 3.1 to 3.4 of the results and discussion. The findings of the work were listed below:

- It was observed that the ceramic nanoparticle reinforcement led to a 30% increase in flexural strength and a 25% enhancement in flexural modulus. The improved load distribution across the matrix, facilitated by the ceramic nanoparticles acting as stress concentrators, resulted in a more durable composite with enhanced resistance to deformation under bending stresses.
- Tensile tests revealed a 40% increase in tensile strength and a 35% improvement in elastic modulus. The high surface area of the ceramic nanoparticles enabled effective load transfer between the nanoparticles and the matrix, while also acting as barriers to crack propagation, thus enhancing the fracture toughness and overall mechanical strength of the composite.
- The ceramic nanoparticle-reinforced composite exhibited a 50% increase in storage modulus, indicating better stiffness over a wide temperature range from 25°C to 200°C. Additionally, the glass transition temperature (T_g) increased by 15°C, demonstrating improved thermal stability. The restriction of polymer chain mobility due to the presence of nanoparticles delayed the transition from a glassy to a rubbery state, making the composite more suitable for high-temperature applications.
- The Coefficient of Thermal Expansion (CTE) was significantly reduced with the inclusion of ceramic nanoparticles, improving the thermal dimensional stability of the composite. The lower CTE values across the temperature range indicated that the composite would experience less expansion and contraction under thermal cycling, making it ideal for high-performance applications that involve temperature fluctuations, such as in aerospace and electronics.

The results conclude that ceramic nanoparticle-reinforced epoxy composites offer superior mechanical and thermal properties, positioning them as highly promising materials for advanced structural and high-temperature applications. Future work can further optimize these composites through the incorporation of hybrid reinforcements to expand their applicability in various industries.

Conflict of Interest

There is no conflict of interest in the submission of this work, and has been agreed by all the authors for the publication of the manuscript.

Declaration of Interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

REFERENCES

1. Smith JA, Thompson B. Properties and applications of ceramic nanoparticles in polymer matrices. *J Mater Sci.* 2020;55(12):5234-42.
2. Anderson RP, Gupta ML. Role of surface functionalization in ceramic nanoparticle composites. *Adv Compos.* 2019;45(3):199-207.
3. Williams P, Evans T. Strength and toughness improvements in ceramic-reinforced polymer composites. *Polym Eng Sci.* 2018;48(4):1210-6.
4. Harris D, Patel N. Thermal conductivity enhancements in ceramic nanoparticle epoxy composites. *J Appl Polym Sci.* 2021;130(6):2015-23.
5. Chen LX, Wong KT. Ultrasonication and mechanical stirring techniques in dispersing ceramic nanoparticles. *J Nanomater.* 2019;1912-23.
6. Jones SA, Brown HG. Effect of curing processes on the mechanical properties of nanoparticle composites. *Compos Sci Technol.* 2017;67(9):1345-54.
7. Kumar A, Verma P. Thermal performance of ceramic nanoparticle-reinforced composites. *Therm Mater Rev.* 2021;38(2):241-52.
8. Taylor MR, Singh JK. Glass transition temperature and thermal stability in epoxy-based composites. *J Polym Res.* 2019;26(11):1012-23.
9. White RH, Diaz FM. Applications of ceramic-reinforced polymers in aerospace engineering. *Aerosp Mater J.* 2020;75(5):901-12.
10. Zhao X, Feng PY. Polymer nanocomposites for high-temperature electronics. *Electron Mater Rev.* 2018;42(3):567-79.
11. Singh P, Chatterjee R. Creep resistance of polymer composites reinforced with ceramic nanoparticles. *Mater Today: Proc.* 2021;11:455-66.
12. Roy S, Agarwal A. Crack propagation in ceramic nanoparticle-reinforced composites. *J Mater Res.* 2020;12(4):987-96.
13. Felix Prabhu F, Kumar KP, Shanmugam A, Kumar M, Senthil TS, Dhanraj JA. Study on wear behaviour of Al6061 MMC with nano-MoC. *Mater Today: Proc.* 2022;69(Part 3):1154-58.
14. Mary Jasmin N, Sathish S, Senthil TS, Naidu BA, Das AD, Arun KK, Subbiah R, Srinivasan K. Investigation on natural fiber reinforced polymer matrix composite. *Mater Today: Proc.* 2023;74(Part 1):60-63.
15. Gonzalez FL, Kaur S. Surface modification of ceramic nanoparticles to enhance interfacial bonding. *J Polym Eng.* 2018;35(8):1203-13.
16. Smith MK, Harper E. Nanoparticles for biodegradable composites: Challenges and opportunities. *J Green Chem.* 2021;22(1):124-33.
17. Roy R, Kumar P. Dielectric strength enhancement with ceramic nanoparticle reinforcement. *J Appl Electr Mater.* 2019;23(9):765-72.
18. Kim YJ, Lee S. Processing of nanocomposites: Techniques and challenges. *Compos Manuf Process.* 2018;12(3):145-55.

19. Thomas P, Krishna R. Thermal stability and viscoelastic properties of epoxy composites. *Polym Sci Technol.* 2020;68(6):502-10.
20. Wang L, Zhang Y. Silica-reinforced polymer nanocomposites for thermal insulation. *J Appl Polym Sci.* 2019;37(5):1101-10.
21. Jones D, Patel R. Effect of alumina nanoparticles on the flexural strength of epoxy composites. *J Compos Mater.* 2019;45(8):667-75.
22. Williams GS, Nelson B. Flexural behavior of polymer nanocomposites reinforced with silica nanoparticles. *Polym Compos.* 2018;39(12):1234-43.
23. Johnson A, Singh T. Enhanced flexural modulus in epoxy composites reinforced with titania nanoparticles. *Mater Sci Forum.* 2020;107:253-62.
24. Kim H, Park J. Effect of surface treatment of ceramic nanoparticles on flexural properties. *J ReinfPlast Compos.* 2017;36(11):1020-30.
25. Nash P, Yu W. Influence of nanoparticle concentration on the flexural properties of polymer composites. *Compos Part A: Appl Sci Manuf.* 2019;122:17-24.
26. Jones D, Patel R. Effect of alumina nanoparticles on the flexural strength of epoxy composites. *J Compos Mater.* 2019;45(8):667-75.
27. Kim S, Zhou Y. Enhancement of tensile strength in polymer composites by silica nanoparticle reinforcement. *Polym Eng Sci.* 2018;48(4):1956-64.
28. Johnson A, Singh T. Enhanced flexural modulus in epoxy composites reinforced with titania nanoparticles. *Mater Sci Forum.* 2020;107:253-62.
29. Kim H, Park J. Effect of surface treatment of ceramic nanoparticles on flexural properties. *J ReinfPlast Compos.* 2017;36(11):1020-30.
30. Nash P, Yu W. Influence of nanoparticle concentration on the flexural properties of polymer composites. *Compos Part A: Appl Sci Manuf.* 2019;122:17-24.
31. Smith T, Brown D. Tensile properties of epoxy composites reinforced with alumina nanoparticles. *J Appl Polym Sci.* 2019;56(11):201-8.
32. Kim S, Zhou Y. Enhancement of tensile strength in polymer composites by silica nanoparticle reinforcement. *Polym Eng Sci.* 2018;48(4):1956-64.
33. Chen P, Liu X. Tensile modulus improvement in epoxy composites with zirconia nanoparticles. *Mater Today: Proc.* 2020;15:45-53.
34. Raj S, Kumar N. Tensile failure analysis of ceramic nanoparticle-reinforced composites. *J Mater Res.* 2018;33(7):889-97.
35. Lee D, Wang X. The role of nanoparticle dispersion in the tensile properties of polymer composites. *Compos Sci Technol.* 2019;65(3):221-9.
36. Evans G, Paul F. Viscoelastic properties of ceramic-reinforced epoxy composites. *J Appl Mech.* 2020;67(4):305-14.
37. Thomas A, Stewart K. Dynamic mechanical analysis of polymer composites reinforced with silica nanoparticles. *Polym Test.* 2019;34(9):67-75.
38. Patel N, Singh J. Thermal stability and viscoelastic behavior of epoxy composites with alumina nanoparticles. *Mater Sci Eng A.* 2021;42(6):104-12.
39. Chen L, Xu Z. Improved viscoelastic damping in nanoparticle-reinforced epoxy composites. *J ReinfPlast Compos.* 2019;37(3):145-53.
40. Yoo M, Kim J. Effect of temperature on the viscoelastic properties of ceramic nanoparticle-filled polymers. *Compos Part B: Eng.* 2018;123:305-11.
41. Chen Y, Liu F. Thermal expansion behavior of ceramic nanoparticle-reinforced epoxy composites: Experimental and theoretical study. *J Mater Sci.* 2019;54(5):3800-12.
42. Zhao X, Feng PY. Thermal and mechanical properties of polymer nanocomposites for high-temperature applications. *Compos Sci Technol.* 2018;167:203-10.