

Advancements In Al6061 Metal Matrix Composites: The Role of SiC, Al₂O₃, and Graphite Reinforcements in Enhancing Properties and Applications

Sneha.H.Dhoria^{1,*}, D. Madhavi², K. Nagalakshmi³, Shaik Jani Basha⁴, A.Muddu⁵

Abstract

Al6061-based metal matrix composites (MMCs) reinforced with silicon carbide (SiC), graphite (Gr), and aluminum oxide (Al₂O₃) exhibit a unique combination of mechanical, thermal, and tribological properties, making them highly suitable for advanced engineering applications. SiC enhances hardness, wear resistance, and load-bearing capacity, while Al₂O₃ improves thermal stability and mechanical strength. Graphite provides self-lubricating properties, reduces friction, and lowers the composite's density, improving fatigue resistance. The synergy of combining these reinforcements in an Al6061 matrix creates hybrid composites with significantly superior performance compared to single-reinforcement systems. This review compares research findings on single-reinforcement composites (Al6061 + SiC, Al6061 + Al₂O₃, and Al6061 + Gr), highlighting the individual advantages and limitations of each reinforcement. Furthermore, hybrid combinations of these reinforcements demonstrate synergistic effects that enhance mechanical, thermal, and tribological properties, emphasizing their potential to address next-generation engineering challenges. These composites are particularly suited for critical applications, including lightweight, high-strength components in aerospace, wear-resistant parts in automotive systems, heat exchangers in marine environments, and durable materials for military-grade equipment. Key advantages include improved wear resistance, better thermal conductivity, reduced weight, and extended service life under extreme conditions. Future research opportunities focus on optimizing reinforcement ratios, refining fabrication techniques, and broadening the industrial adoption of these hybrid composites.

Keywords: SiC, Al₂O₃, graphite, aluminum metal matrix composites, aluminium hybrid composites

*Author for Correspondence

Sneha.H.Dhoria
E-mail: snehadhoria@gmail.com

^{1,5}Assistant Professor, Department of Mechanical Engineering, R.V.R & J.C. College of Engineering, Chowdavaram, Guntur, Andhra Pradesh, India

²Associate Professor, Department of Physics, R.V.R&J.C College of Engineering, Chowdavaram, Guntur, Andhra Pradesh, India

³Assistant Professor, Department of Physics, R.V.R & J.C. College of Engineering, Chowdavaram, Guntur, Andhra Pradesh, India

⁴Associate Professor, Dept. of S & H (Physics), Loyola Institute of Technology and Management, Dhullipala, Andhra Pradesh, India

Received Date: January 02, 2025

Accepted Date: March 21, 2025

Published Date: April 17, 2025

Citation: Sneha.H.Dhoria, D. Madhavi, K. Nagalakshmi, Shaik Jani Basha, A.Muddu. Advancements in Al6061 Metal Matrix Composites: The Role of SiC, Al₂O₃, and Graphite Reinforcements in Enhancing Properties and Applications. Journal of Polymer & Composites. 2025; 13 (3): 90–98p.

INTRODUCTION

Aluminium alloys remain extensively habituated in various applications owing to its profitable for their characteristics of the material. [1] Numerous aluminium alloys have been developed as a result of the in-depth research done with the aim of enhancing the particular material properties that are needed. Composites are multiphase materials made of reinforcement and matrix that were produced to happen the developing prerequisite for visually attractive engineering materials. Composites typically have exceptional mechanical qualities, such as increased hardness, fracture toughness, improved resistance to corrosion and wear, strength along with excellent thermal properties. Composite materials have turn out to be further widespread in industrial uses as a result of these beneficial properties [2]. Extensive research has led to the

improvement of numerous aluminium alloys tailored to encounter definite material necessities. Diverse categories of engineering materials are illustrated in Figure 1. Numerous aluminium alloy series have been developed to enhance specific characteristics.

Composites are classified according to matrix material. Some are polymer matrix composites (PMCs), some are ceramic matrix composites (CMCs), and others are metal matrix composites (MMCs). Of these, MMCs have wider industrial application due to having a better approach for industrial usage over PMCs and CMCs. [3]. MMCs employ several major matrix phases, such as magnesium, titanium, aluminum and copper matrix composites [4]. When added to traditional fiber-reinforced polymer composites, metal fibers create a strong and ductile composite that reduces material cost and weight compared with metal-based structures [5]. An approach of noble-metal-free nanostructured electrocatalysts for overall water splitting is another novel way for metallic composites [6]. Aluminium matrix composites (AMCs), a subset of MMCs, integrate various reinforcements in specific proportions to achieve tailored performance enhancements. AMCs are manufactured using diverse techniques to suit applications. Within MMCs, the metal matrix serves as the continuous phase, distributing and transmitting loads to the dispersed reinforcement phase [7]. AMCs, which use pure aluminium or its alloys as the matrix, are progressively employed in industrial settings due to their exceptional tribological, material, and mechanical characteristics. Research has focused on developing AMCs by incorporating different aluminium alloys as matrices with various reinforcements to achieve desired properties [8].

Aluminium alloys from the 6xxx series, with silicon and magnesium as primary alloying elements, are particularly favoured in the aviation and locomotive industries for their excellent strength to weight ratio, corrosion and wear resistance, formability, weld ability, and cost-effectiveness [9]. Al6061, a widely used alloy in aluminium matrix composites, offers numerous advantages, including moderate density, corrosion resistance, good machinability and high strength. However, its relatively low wear resistance limits its applications. Reinforcements such as SiC, Al₂O₃ and graphite, when combined with aluminium alloys, enhance their strength-to-weight ratio and resistance to wear and corrosion, making them ideal for automotive and aerospace applications [8, 9]. Recently, HMMC based on aluminium (Al) have gained popularity in these industries due to their lightweight, high strength, toughness, and improved mechanical properties [10].




Figure 1. Different Categories of Engineering Materials.

Al-6061 HMMC is a composite material that contains multiple reinforcement types, which can be either inorganic or organic. Secondary reinforcements in the matrix are responsible for the exceptional properties that these composites are designed to achieve. Aluminium hybrid materials demonstrated superior mechanical characteristics and thermal expansion coefficients. Stir-casting is a widely used technique for creating hybrid materials based on aluminium. The quantity and kind of constituent materials of hybrid composites can be scientifically optimized to change material properties [11]. When various reinforcements were used in hybrid MMC, mechanical properties increased; however, after a particular amount of reinforcement, they began to decrease. As a result, reinforcements should only be added up to a certain weight fraction; beyond that, they serve no purpose. Since the ideal weight percentage of reinforcement varies with each composite, it can be assumed that this is because of greater porosity and agglomeration at increased reinforcement content. Aluminium hybrid nano composites are additionally created using stir-casting approaches. The mechanical, microstructural, and tribological qualities of composites are improved by the addition of appropriate reinforcements in the right amounts [12].

Silicon carbide is widely worn as a reinforcement material in MMC due to its high hardness, high thermal conductivity, and outstanding wear resistance. The incorporation of SiC in a metal matrix improves the mechanical properties of the composite, including strength and stiffness, and thus it is applied to applications requiring high-performance materials, in various industries. [13] SiC also enhances the resistance of the composite to high-temperature environments and corrosion. Moreover, low density contributes to a high strength-to-weight ratio; hence, SiC-reinforced MMCs are especially suitable for lightweight structural components. The SiC reinforcement with Al6061 MMC helps in enhance of components performance in demanding conditions for manufacturing parts such as engine components, turbine blades, and heat exchangers, brake rotors, pistons, and cylinder heads, propeller blades, and hulls.

Alumina, or aluminum oxide (Al_2O_3), is the utmost used reinforcement materials in MMC because of its excellent hardness, high wear resistance, and good thermal stability. As reinforcement, Al_2O_3 gives the composite a significant enhancement of its mechanical properties, including strength, stiffness, and abrasion resistance. It also provides excellent thermal conductivity and corrosion resistance, accomplishing advisable for hard and high-temperature situations. The composites reinforced with Al_2O_3 have found widespread applications in automobile, aerospace, and electronics sectors, where durability, strength, and thermal management play a significant role. [14] Additionally, it is relatively cheaper and readily available for several industrial applications. The Alumina reinforcement with Al6061 MMC offers good thermal and wear resistance that helps in in manufacturing of brake discs and landing gears that are exposed to high temperatures and friction, underwater hulls, armor systems, bearings, rotor parts etc.

Graphite is widely used as reinforcement in MMCs owing to its specific properties: high lubricant, low density, and good thermal conductivity. In a composite as reinforcement, graphite will surge the wear of the composite by reducing friction, improving the material's sliding contact endurance in service applications, and providing thermal stability and improved thermal conductivity; hence, graphite-reinforced composites are highly recommended for use in high temperature. Graphite is mainly advantageous in applications like automotive engine components, bearings, and aerospace materials where weight reduction, thermal management enhancement, and superior wear properties are required.[15] Additionally, it is valuable because of its self-lubricating nature, which can reduce the need for external lubrication in certain applications. The Graphite reinforcement with Al6061 MMC provides excellent lubrication and reduces wear, suitable for manufacturing of sliding components, seals, bearings, brake pads, piston rings, etc.

Depending on the intended qualities and use of the composite, different production processes, including casting, stir casting, hot pressing, and powder metallurgy are used to create metal matrix composites (MMCs). Stir casting stands out among these due to its affordability and ease of use. To

ensure even dispersion of the reinforcement inside the matrix, stir casting involves adding the reinforcement particles to a molten metal matrix while stirring. [16] This technique is popular for creating aluminum-based MMCs, such as Al6061, since it can successfully integrate different reinforcements like SiC, graphite, and Al₂O₃. Stir casting has the benefit of producing huge, intricate shapes at comparatively low prices, which makes it perfect for applications requiring lightweight, very durable components in different sectors of industry.

The novelty of using a review on Al6061 reinforced with three different reinforcements—SiC, graphite, and Al₂O₃—individually lies in the unique combination of properties that each reinforcement brings to the composite, and their potential to address specific performance requirements in various industries. SiC, with its exceptional hardness and wear resistance, enhances the mechanical strength and durability of the Al6061 matrix, accomplishing it optimal for high-load, abrasive operations. Graphite, known for its self-lubricating properties and excellent thermal conductivity, improves the composite's frictional behavior and thermal management, making it suitable for high-temperature and low-wear environments. Al₂O₃, with its superior hardness, thermal stability, and corrosion resistance, contributes to the composite's overall strength, wear resistance, and performance in harsh environments. By reviewing the individual impacts of these reinforcements, this work highlights how different reinforcements can be strategically selected to tailor Al6061-based composites for specific applications, offering a deeper understanding of their individual and combined potential in industries like aerospace, automotive, and electronics.

Al6061- SiC Composites

In Al6061-SiC composites, silicon carbide (SiC) particles are included into the Al6061 matrix to advance its mechanical and thermal characteristics. [17] The hardness, wear resistance, and tensile strength of the composite are significantly increased with the inclusion of SiC, which makes it perfect for operations necessitating high strength and durability under stress. SiC reinforcement further improves the composite's dimensional stability and thermal conductivity, which qualifies it for high-temperature applications. These composites are extensively used in manufacturing, automobile, and aircraft industries, especially in elements like heat exchangers, brake discs, and engine parts where strong yet lightweight materials are needed. Al6061-SiC composites are very appealing for lowering vehicle weight and improving fuel efficiency due to their superior strength-to-weight ratio and exceptional wear resistance.

Al6061- Graphite Composites

Al6061-Graphite composites combine the lubricating and thermal qualities of graphite as reinforcement with the lightweight and ductile characteristics of the Al6061 matrix. Graphite is ideal for operations requiring sliding or rotating parts because it improves the composite's self-lubricating qualities, reduces abrasion, and boosts resistance to wear. The exceptional thermal conductivity of graphite aids in heat dissipation, which is especially advantageous in hot conditions. These composites are extensively utilised in tribological, automobile, and aerospace areas including engine components, bearings, and pistons, where friction, wear resistance, and thermal management low are essential. Al6061-Graphite composites are also beneficial in applications where longer component life and less maintenance are crucial because graphite is self-lubricating, reducing the need for external lubrication.[18]

Al6061-Al₂O₃ Composites

Al6061-Al₂O₃ composites combine the hardness, wear resistance, and thermal stability of aluminum oxide (Al₂O₃) as reinforcement with the lightweight and high-strength characteristics of the Al6061 matrix. Al₂O₃ greatly improves the composite's hardness, tensile strength, and corrosion and wear resistance, making it appropriate for use in abrasive and harsh environments [19]. These composites can function dependably in high-temperature applications because of their exceptional thermal stability. Al6061-Al₂O₃ composites are extensively utilized in structural, automotive, and aerospace applications where strength, durability, and resistance to harsh environments are essential, such as armor plating,

heat exchangers, and engine components. Furthermore, these composites' high stiffness and low weight make them perfect for weight-sensitive applications, which enhance advanced engineering performance and energy efficiency. [20]

Most of the ceramic reinforcements (silicon carbide, alumina) have lower thermal conductivity than Al6061. When these are incorporated with the aluminium matrix, they tend to lower the overall thermal conductivity of the metal matrix composite. This can be beneficial where heat dissipation needs to be controlled such as electronic and insulation components. Fiber reinforcements (carbon) also exhibit lower thermal conductivity than the Al6061 alloy metal depending upon their alignment direction.

Thermal expansion refers to change in the material dimensions in response to temperature changes. The incorporation of ceramic reinforcements to Al6061 metal matrix composite, they gradually reduce the overall thermal expansion of the material. This helps the dimensional stability across the temperature variations, particularly in aerospace and automotive parts that experience wide temperature changes. Fiber reinforcements like carbon fibers have lower coefficient of thermal expansion than the ceramic reinforcements. This exhibits the overall reduction in thermal expansion with aligned load direction of the composite material and becomes more stable under temperature fluctuations such as in high performance aerospace structures.

Al6061 MMCs exhibits improved mechanical properties such as high strength and stiffness as compared to pure base material Al6061 alloy. Enhanced wear resistance makes these materials ideal for high-wear environments like automotive engine components. Fatigue resistance makes them suitable for dynamic loading conditions. Light weight reinforcements can maintain or even reduce the overall weight of the composite while still improving mechanical properties. This is crucial for aerospace and automotive industries, where weight reduction is essential for fuel efficiency and performance. Improved thermal conductivity which is beneficial in heat-sensitive applications like heat exchangers or electronic packaging. Corrosion resistance making them suitable for marine, automotive, and other outdoor applications. Sports equipment like bicycles and golf clubs due to their strength-to-weight ratio.

Al6061 HMMC's

Al6061 HMMCs combine the versatile properties of the Al6061 alloy with multiple reinforcements, like SiC, graphite, and Al₂O₃, to achieve a synergistic improvement in mechanical, thermal, and tribological characteristics. Graphite contributes self-lubricating qualities and lowers friction, SiC increases hardness and durability, and Al₂O₃ improves strength, thermal stability, and corrosion resistance. These hybrid materials combine the advantages of each of the constituent reinforcements.[21] The combination of these reinforcements allows Al6061 HMMCs to exhibit superior performance compared to composites with a single reinforcement, making them highly suitable for demanding applications in aerospace, automotive, and defense industries.[22] The tailored properties, such as a high strength-to-weight ratio, excellent wear resistance, and thermal management capabilities, make Al6061 HMMCs ideal for lightweight, high-performance components like engine parts, brake rotors, bearings, and structural components. The ability to customize reinforcement proportions further enhances their versatility, meeting the specific needs of diverse engineering applications.

This research explores the effects of incorporating graphite, SiC, and Al₂O₃ as reinforcements in Al6061 composites using the stir casting process. The study aims to show the review on one reinforcement and later develop a HMMC with enhanced mechanical properties and evaluate its performance. By investigating the combination of these reinforcements, this study seeks to provide valuable insights into the potential for improving the characteristics of Al6061 composites and advancing their applications. Table.1 [23-33] provides an overview of the study investigations conducted on Sic, Gr and Al₂O₃ reinforcements and also with different AA 6061 composites comprising one or more hybrid reinforcements.

Table 1. Summary of research studies on Al6061, SiC, Gr., and Al₂O₃ as single reinforcements and hybrid composites.

Alloy	Reinforcements	Method	Properties	Conclusion	Ref.
Al6061	SiC (0,2,4,6 wt %) micro particles	Ultrasonic stir casting	Mechanical, Tribological, corrosion	SiC reinforcement in Al6061 alloy enhances hardness and tensile strength by 33%, but decreases elongation by 42%. The composite with 6% SiC also performs well in dry sliding wear and corrosion resistance, which is used for engineering applications.	23
Al6061	SiC (5-10 wt %)	Stir casting	Mechanical and Wear properties	SiC addition can significantly enhance the Al6061 based properties with 7.5 wt% being the most effective concentration for optimal performance.	24
Al6061	SiC, Graphite	Stir casting	Machining (EDM)	The impact of optimizing EDM parameters and utilizing cryogenic treatment to improve the surface finish of aluminum metal matrix composites. These insights can guide future research and practical applications in the field of advanced manufacturing.	25
Al6061	SiC, Gr(2-8%)	Stir casting	Mechanical and Tribological	6wt.% of hybrid reinforcement shows substantial development in hardness by 30%, whereas tensile strength by 10.82%, compressive strength by 68.14%, and flexural strength by 85% in comparison to base metal.	26
Al6061	SiC (5%,10%,15%)Gr. (10%)	Stir casting process	Mechanical, Wear	SiC reinforcement in Al6061 alloy boosts hardness and tensile strength by 33%, while reducing elongation by 42%. The 6% SiC composite excels in wear and corrosion resistance, ideal for engineering uses.	27
Al6061	SiC(0-9wt %)Gr-1wt %	Liquid metallurgy	Mechanical, Microstructure	EDX and SEM confirmed uniform SiC and Gr distribution in Al6061, proving successful fabrication. Al6061-9wt% SiC-1wt% Gr composites showed greater hardness, tensile strength, and wear resistance, aiding aluminum alloy MMC model development.	28
Al6061	Graphite(9 wt%),Al ₂ O ₃ (9 wt%)	Liquid stir casting	Mechanical	Composites made of graphite and Al6061-9wt% Al ₂ O ₃ shown superior tensile strength and hardness, with the latter also showing greater elongation.	29
Al6061	Al ₂ O ₃ nano composites (1-5 vol %)	Milling	Mechanical and Tribological	Nanocomposites with 3 vol% Al ₂ O ₃ achieved an extreme hardness of 235 HV and an optimal wear rate of 4×10^3 mg/m. Increasing Al ₂ O ₃ to 5 vol% decreased hardness to 112 HV and increased wear rate.	30
Al6061	Al ₂ O ₃ , graphite and hybrid Al ₂ O ₃ and graphite	Friction stir processing	Mechanical	AA 6061/ (Al ₂ O ₃ , Gr, and Al ₂ O ₃ +Gr) surface composites were fabricated using friction stir processing, achieving homogeneous particle distribution and increased hardness and UTS with nano-scale Al ₂ O ₃ , especially after T6 heat treatment and the third pass.	31
Al6061	SiC, Al ₂ O ₃ (2.5,5 wt %)	Stir casting	Mechanical	Al6061 with 5 % of SiC and 2.5 % of Al ₂ O ₃ has the superior mechanical properties than the other two compositions	32,33

Different types of reinforcements are utilized with the AA 6061 matrix to produce aluminum matrix composites (AMCs). Among these, SiC, Al₂O₃, B₄C, ZrO₂, CeO₂, and TiC particulates are widely favored due to their remarkable effectiveness in enhancing composite properties. Stir casting has proven effective for all the reinforcements discussed, as microstructural analyses consistently demonstrate uniform distribution within the matrix. This uniformity ensures strong correlation among the base metal and the reinforcements.

Mechanical testing of these composites reveals improvements in tensile strength, compressive strength, and hardness with increasing reinforcement content. Wear resistance also improves significantly owing to the incorporation of the particles of reinforcement. Additionally, the introduction of reinforcements leads to a reduction in grain size. However, exceeding a certain weight fraction of reinforcement can negatively impact properties owing to issues like increased porosity, particle agglomeration, and uneven distribution. Hybrid AA 6061 composites, incorporating two or more types of reinforcements, have shown superior performance. The selection of reinforcement depends on the specific properties required. The study suggests that the addition of secondary reinforcements later enhances the overall properties of the composites.

CONCLUSIONS

The review highlights the advancements in producing Al6061-based MMCs using the stir casting process, a widely adopted and cost-effective fabrication method. Al6061, a versatile aluminum alloy, has been reinforced with materials like SiC, Al₂O₃, and graphite, each contributing unique properties:

- *SiC*: Enhances hardness and wear resistance,
- *Al₂O₃*: Improves thermal stability and mechanical strength,
- *Graphite*: Reduces density and provides lubrication and fatigue resistance.
- Hybrid Al6061 composites, which combine these reinforcements, demonstrate superior mechanical, tribological, and corrosion resistance properties compared to single-reinforcement composites, accomplishing them more suitable in aerospace, automotive, marine, and military sectors.
- The stir-casting process's effectiveness depends on parameters like stirrer speed, stirring duration, blade design, reinforcement size, and melt temperature. While this method has been used successfully to incorporate industrial waste materials like fly ash into composites, contributing to environmental sustainability, challenges such as porosity and reinforcement agglomeration remain.
- Although hybrid composites with SiC, Al₂O₃, and graphite have shown promise, limited research exists on their combination.
- Future studies should focus on optimizing the fabrication of hybrid metal matrix nanocomposites (MMNCs) using advanced techniques like ultrasonic-assisted stir casting and squeeze casting.
- These methods can address current challenges by minimizing porosity and ensuring a uniform distribution of reinforcements, thereby unlocking the full potential of these materials for advanced engineering applications.

Acknowledgements

The authors declare that there are no acknowledgements to be made for this study. All research and writing were conducted independently without external support or contributions.

Declaration of Interest

Authors declare that there are no conflicts of interest associated with this publication all authors have contributed to the research and writing of this manuscript, and no financial or personal relationships could be perceived as influencing the work reported in this manuscript.

REFERENCES

1. You X, Xing Z, Jiang S, et al. A review of research on aluminum alloy materials in structural engineering. *Develop Built Environ* 2024;100319.
2. Abdudeen A, Mourad A-HI, Qudeiri JA, et al. Evaluation of characteristics of A390-SiCp squeeze cast and gravity cast composites. *Proc 2020 Adv Sci Eng Technol Int Conf (ASET), Dubai, UAE* 2019;1–6.
3. Gopalakrishnan S, Murugan N. Production and wear characterization of AA 6061 matrix titanium carbide particulate reinforced composite by enhanced stir casting method. *Compos Part B* 2012; 43:302–308.
4. Praveen Kumar M, Mangalaraja RV, Karazhanov S, de Oliveira TF, Sasikumar M, Murugadoss G, Mubarak S, Palanisamy S, Kumaresan N. An overview of noble-metal-free nanostructured electrocatalysts for overall water splitting. *Materials Technology for the Energy and Environmental Nexus*, Volume 1. 2023 Sep 1:3-1.
5. Aruchamy K, Sampath PS, Bhuvaneshwaran M, Umachitra G, Palanisamy S, Mubarak S. Metallic fibers: applications and composites. In *Synthetic and Mineral Fibers, Their Composites and Applications* 2024 Jan 1 (pp. 433-460). Woodhead Publishing.
6. Mohankumar V, Kapilan S, Karthik A, Bhuvaneshwaran M, Santulli C, Kumar DT, Palanisamy S, Fragassa C. A hybrid design of experiment approach in analyzing the electrical discharge machining influence on stir cast Al7075/B4C metal matrix composites. *Metals*. 2024 Feb 7;14(2):205.
7. Ravindran S, Mani N, Balaji S, et al. Mechanical behaviour of aluminium hybrid metal matrix composites – a review. *Mater Today Proc* 2019;16:1020–1033.
8. Pandey U, Purohit R, Agarwal P, et al. Study of fabrication, testing and characterization of Al/TiC metal matrix composites through different processing techniques. *Mater Today Proc* 2018;5:4106–4117.
9. Mukhopadhyay P. Alloy designation, processing, and use of AA6XXX series aluminium alloys. *ISRN Metall* 2012;2012.
10. Basavarajappa S, Chandramohan G, Mukund K, et al. Dry sliding wear behavior of Al 2219/SiCp-Gr hybrid metal matrix composites. *J Mater Eng Perform* 2006;15:668–674.
11. Papabathina MR, Chinka SS, Putta NR, et al. Effect of graphite on mechanical and tribological properties of Al6061/SiC hybrid composites. *Ann Chim Sci Mat* 2023;47(3).
12. Panwar N, Chauhan A. Fabrication methods of particulate reinforced aluminium metal matrix composite – a review. *Mater Today Proc* 2018;5(2):5933–5939.
13. Basavarajappa S, Chandramohan G, Davim JP. Application of Taguchi techniques to study dry sliding wear behaviour of metal matrix composites. *Mater Des* 2007;28(4):1393–1398.
14. Simões S. High-performance advanced composites in multifunctional material design: State of the art, challenges, and future directions. *Materials* 2024;17(23):5997.
15. Kavimani V, Gopal PM, Thankachan T, et al. Evolution and recent advancements of composite materials in thermal applications. In: *Applications of Composite Materials in Engineering*. Elsevier Science Ltd; 2025:119–138.
16. Wang R, Zhang F, Yang K, et al. Important contributions of carbon materials in tribology: From lubrication abilities to wear mechanisms. *J Alloys Compd* 2024;173454.
17. Sharma SK, Saxena KK, Salem KH, et al. Effects of various fabrication techniques on the mechanical characteristics of metal matrix composites: a review. *Adv Mater Process Technol* 2024;10(2):277–294.
18. Mantha SR, Veeresh Kumar GB, Pramod R, et al. Studies of SiC-filled Al6061 metal matrix composite optical, mechanical, tribological, and corrosion behavior with strengthening mechanisms. *Adv Eng Mater* 2024;2401997.
19. Khatkar SK, Suri NM, Kant S, et al. A review on mechanical and tribological properties of graphite reinforced self-lubricating hybrid metal matrix composites. *Rev Adv Mater Sci* 2018;56(1):1–20.
20. Koli DK, Agnihotri G, Purohit R. A review on properties, behaviour and processing methods for Al-nano Al₂O₃ composites. *Procedia Mater Sci* 2014;6:567–589.
21. Sypeck DJ, Wadley HN. Cellular metal truss core sandwich structures. *Adv Eng Mater* 2002;4(10):759–764.

22. Sharath BN, Madhu P, Verma A. Enhancing tribological performance: A review of ceramic reinforced aluminium hybrid composites for high-temperature engineering applications. *Hybrid Adv* 2023;100094.
23. Kumar R, Bairwa KN. Optimizing Al6061-based hybrid metal matrix composites: Unveiling microstructural transformations and enhancing mechanical properties through Ni and Cr reinforcements. 2023; 2161–2172.
24. Subrahmanya R, Viswanath M, Mantha GB, Veeresh Kumar RB, Pramod CS, Rao. Studies of SiC-filled Al6061 metal matrix composite optical, mechanical, tribological, and corrosion behavior with strengthening mechanisms. *Adv Eng Mater* 2024; doi: 10.1002/adem.202401997.
25. Amit D, Sagar K, Maneesh D. Evaluating the effect of different percentage addition of SiC on mechanical and wear properties of Al6061 composite. *Macromol Symp* 2024; doi: 10.1002/masy.202300164.
26. Rajwinder SG, Partap SS, Samra P, Kumar A. Effect of Electrical Discharge Machining Parameters and Cryogenic Treatment on Surface Roughness of Aluminum Metal Matrix Composite (Al6061/SiC/Graphite). *CGC Int J Contemp Technol* 2024;6(2):415–421. doi: 10.46860/cgcijctr.2024.06.10.415
27. Papabathina MR, Chinka SSB, Putta NR, et al. Effect of graphite on mechanical and tribological properties of Al6061/SiC hybrid composites. *Ann Chim Sci Mat* 2023;47(3).
28. Ibrahim S, Abdel Ghafaar M, Abdel-Hamid IM, et al. Stir casted SiC-Gr/Al6061 hybrid composite tribological and mechanical properties. *J Mater Sci: Mater Electron* 2020;2(5):1–8. doi: 10.1007/S42452-020-2713-4.
29. Gouda S, Kumar GV, Pramod R, et al. Fabrication, mechanical and wear properties of Aluminum (Al6061)-silicon carbide-graphite Hybrid Metal Matrix Composites. *Frattura ed Integrità Strutturale* 2022;16(62):134–149.
30. Nagaraal M, Shivananda BK, Auradi V, et al. Mechanical behavior of Al6061-Al₂O₃ and Al6061-graphite composites. *Mater Today Proc* 2017;4(10):10978–10986.
31. Hosseini N, Karimzadeh F, Abbasi MH, et al. Tribological properties of Al6061–Al₂O₃ nanocomposite prepared by milling and hot pressing. *Mater Des* 2010;31(10):4777–4785.
32. El-Eraki BR, El-Sissi AR, Khafagi SM, et al. Process parameters optimization for producing AA6061/(Al₂O₃, Gr and Al₂O₃+ Gr) surface composites by friction stir processing. *Int Conf Aerosp Sci Aviat Technol* 2019;18(18):1–13.
33. Kumar SR, Ramakrishnan S, Risvak M, et al. Experimental analysis and characterization of mechanical, physical properties of Aluminium (Al6061) metal matrix composite reinforced with SiC and Al₂O₃ using Stir casting. *IOP Conf Ser Mater Sci Eng* 2021;1145(1):0121.