STM JOURNALS

International Journal of
Fracture Mechanics and Damage Science

Volume 3, Issue 2, 2025
July–December
DOI (Journal): 10.37591/IJFMDS

https://journals.stmjournals.com/ijfmds

Review IJFMDS

Phase-Field Modeling of Brittle and Ductile Fracture Under Complex Loading Conditions

Nidhi Sahu*

Abstract

Phase-field modeling has emerged as a powerful computational framework for predicting fracture behavior in engineering materials, offering a unified description of crack initiation, propagation, branching, and coalescence without the need for explicit crack tracking. This study presents an in-depth examination of phase-field modeling applied to both brittle and ductile fracture under complex loading conditions, including multiaxial stress states, cyclic loading, thermal gradients, and dynamic impact. The phase-field approach regularizes the sharp crack topology through an auxiliary scalar field, enabling smooth numerical representation of damage evolution while naturally capturing discontinuities in displacement. For brittle materials, the method accurately reproduces crack paths driven by tensile stresses and energy minimization, while for ductile materials the framework is extended by incorporating plastic deformation, strain hardening behavior, and rate-dependent dissipation mechanisms. The study highlights the significance of selecting appropriate degradation functions, length-scale parameters, and constitutive laws to ensure physically meaningful predictions across different material classes. Coupled thermomechanical and elastoplastic phase-field formulations are discussed to demonstrate the adaptability of the approach to real-world scenarios such as thermal shock, fatigue crack growth, and fracture in heterogeneous microstructures. Numerical simulations validate the model's capability to capture transitions between brittle and ductile fracture modes and to predict mixed-mode crack propagation under complex boundary conditions. The findings confirm that phase-field modeling provides a versatile, robust, and computationally efficient tool for fracture mechanics, offering improved predictive accuracy for design, safety assessment, and failure analysis in structural, aerospace, automotive, and energy applications.

Keywords: Brittle-fracture, complex loading conditions, crack initiation and propagation, ductile fracture, fracture mechanics, mixed-mode fracture, phase-field modeling

INTRODUCTION

Fracture prediction in engineering materials is a critical challenge because of the inherently complex nature of crack initiation, growth, interaction, and eventual failure under diverse loading conditions. Traditional fracture mechanics approaches, although effective in specific scenarios, often struggle to capture evolving crack topologies, mixed-mode fracture behavior, and interactions between damage mechanisms, especially when materials exhibit both brittle and ductile responses. To address these limitations, the phase-field method has emerged as a robust and versatile computational framework capable of representing fractures as diffused damage zones without the need for explicit crack tracking [1].

***Author for Correspondence**
Nidhi Sahu
E-mail: hinidhigupta1@gmail.com

Research Scholar, Department of Mechanical Engineering, Lingaya's Vidyapeeth, Faridabad, Haryana, India.

Received Date: December 15, 2025
Accepted Date: December 19, 2025
Published Date: December 29, 2025

Citation: Nidhi Sahu. Phase – Field Modeling of Brittle and Ductile Fracture Under Complex Loading Conditions. International Journal of Fracture Mechanics and Damage Science. 2025; 3(2): 13–18p.

© STM Journals 2025. All Rights Reserved

The phase-field approach formulates fracture evolution based on energy minimization principles, where a scalar field governs the transition from an intact to a fully broken material. This diffuse interface representation enables seamless modeling of complex phenomena, such as crack nucleation, branching, merging, and interaction with microstructural heterogeneities. For brittle materials, this method accurately reproduces energy-driven crack propagation, whereas for ductile materials, it can be coupled with plasticity models, strain hardening laws, and rate-dependent effects to capture the interplay between plastic deformation and fracture [2].

Under complex loading conditions, such as multiaxial stresses, cyclic or fatigue loads, dynamic impacts, and thermal gradients, the phase-field model demonstrates significant advantages over conventional methods. Its flexibility allows integration with thermomechanical and elastoplastic formulations, enabling realistic simulation of the fracture behavior encountered in structural components, aerospace systems, automotive parts, and energy devices. Figure 1 shows the relationship between fatigue and fracture [2].

This study explored the theoretical foundations, computational aspects, and application potential of phase-field modeling for brittle and ductile fractures under complex loading, highlighting its growing relevance in predictive material engineering and failure analysis [3].

LITERATURE

Phase-field fracture methods have been developed from variational formulations of fractures that regularize Griffith's sharp crack through a diffused scalar field, enabling spontaneous nucleation, branching, and merging of cracks without explicit tracking. Miehe et al. established a thermodynamically consistent variational framework and incremental formulation that made phase-field fractures viable for practical finite element simulations and dynamic problems [4].

Early numerical and methodological benchmarks focused on brittle, linear-elastic solids and efficient finite element implementations (staggered/monolithic solvers, length-scale regularization, degradation functions). Ambati et al. reviewed these algorithmic developments and proposed efficient finite element treatments and hybrid formulations that addressed numerical stiffness and mesh-dependence in brittle-fracture simulations [5].

Significant effort since mid-2010 has extended phase-field models to ductile fracture by coupling the damage field with elastoplastic constitutive laws, strain hardening, and rate dependence. Variational gradient formulations and large-strain generalizations by Miehe (and collaborators) and Ambati et al. provided frameworks able to capture the competition between plastic dissipation and fracture energy, enabling predictions of ductile crack initiation, shear- driven failure, and brittle-to-ductile transitions [5].



Figure 1. The relation between fatigue and fracture.

© STM Journals 2025. All Rights Reserved

Another rapidly growing branch is fatigue and cyclic loading, where researchers have incorporated history variables, energy-based degradation of fracture toughness, and cycle-aware evolution laws to model both high- and low-cycle fatigue in the brittle and ductile regimes. Recent comprehensive reviews have summarized fatigue-oriented phase-field formulations and their applications in engineering problems [6].

Thermomechanical coupling, rate effects, and multiphysics extensions (hydraulic fracturing, hydrogen embrittlement, and microstructure-informed homogenization) have further broadened applicability but have also raised new challenges: choice and calibration of length-scale and degradation functions, correct partitioning of elastic/plastic energy for damage driving, computational cost for 3D large-scale simulations, and verification against experiments across loading modes. Recent works have proposed mixed-mode ductile models, gradient plasticity regularizations, and homogenization strategies to address these issues [7].

In summary, the literature shows a rapid, multi-directional maturation of phase-field fracture modeling, from robust brittle-fracture solvers to coupled elastoplastic and fatigue formulations that tackle realistic complex loading. The remaining research priorities include improved experimental calibration protocols, efficient multiscale/parallel solvers, and unified frameworks that reliably predict transitions among brittle, ductile, and fatigue failure modes under complex service conditions [8].

METHODOLOGY

The methodology for phase-field modeling (PFM) of brittle and ductile fractures under complex loading conditions involves a systematic sequence of mathematical formulation, constitutive modeling, numerical implementation, and validation. The following steps outline the standard and extended procedures adopted in contemporary research:

Governing Energy Functional

The phase-field model was developed based on a variational formulation of fracture mechanics. The total energy functional Ψcombines elastic (or elastoplastic) strain energy, fracture surface energy, and external work:

$$\Psi = \int_{\Omega} \left[g(\phi)\psi_0(\varepsilon) + \psi_p + G_c \left(\frac{\phi^2}{2\ell} + \frac{\ell}{2} \mid \nabla\phi \mid^2 \right) \right] d\Omega - W_{\text{ext}}$$

where:

- ϕ= phase-field variable (0 = intact, 1 = fully fractured)
- $g(\phi)$= degradation function
- ψ_0= elastic strain energy
- ψ_p= plastic dissipation (ductile model)
- G_c= fracture toughness
- ℓ= length-scale parameter [9]

Phase-Field Evolution Equations

Applying variational calculus yields the coupled partial differential equations governing displacement u and crack evolution ϕ:

$$\nabla \cdot [(1-\phi)^2 \sigma] + \mathrm{b} = 0$$

$$\frac{G_c}{\ell}\phi - G_c \ell \nabla^2 \phi = 2(1-\phi)\psi_0^+$$

© STM Journals 2025. All Rights Reserved

The tensile–compressive decomposition $\psi_0^{\pm}$prevents unphysical crack growth under compressive loading [10].

Ductile Fracture Extension

For ductile materials, additional constitutive features are incorporated:

- Elasto-plasticity (J2 plasticity, strain hardening, rate dependence).
- Plastic energy contribution as a crack-driving force.
- Mixed-mode formulations for shear-dominated ductile fracture.
- Large deformation kinematics for metals and polymers. This produces a coupled damage plasticity formulation [11].

Numerical Implementation

The finite element method (FEM) is used with either:

- *Staggered scheme:* An alternate solution of the displacement and phase-field equations
- *Monolithic scheme:* Solve the coupled system simultaneously for higher stability. Mesh refinement is applied near damage zones based on the length-scale ℓ.

Complex Loading Conditions

The model is tested below:

- Multiaxial tension–compression–shear
- Cyclic/fatigue loading (with fatigue degradation laws)
- Thermomechanical loading (coupled heat conduction)
- Impact and dynamic load (rate-dependent phase-field evolution) boundary conditions were applied based on experimental configurations.

Model Calibration and Validation

Calibration involves tuning the following parameters:

- $G_c$and ℓ, as well as the degradation function
- Plastic parameters (ductile case)
- Fatigue parameters (cyclic loading)

Validation is performed through comparison with: Experimental load–displacement curves.

- Crack paths and fractured patterns.
- Mode-mixity benchmarks (Mode I, II, III).

APPLICATIONS

PFM has become a versatile tool for predicting fracture behavior across a wide range of engineering materials and loading scenarios. Their ability to seamlessly capture crack initiation, propagation, branching, and interaction under complex stress states makes them highly applicable in both research and industrial settings. The key applications include the following.

Structural Engineering

PFM is used to predict failures in concrete, steel, and composite structures under multiaxial loading, seismic forces, or impact events. It accurately models brittle cracking in concrete and mixed-mode fractures in fiber-reinforced composites, enabling optimized structural designs and improved safety assessments.

© STM Journals 2025. All Rights Reserved

Aerospace and Automotive Components

Lightweight metals and alloys in aerospace and automotive industries are prone to both brittle and ductile failure under cyclic, impact, or thermal loading. Phase-field models allow engineers to simulate crack growth in engine components, fuselage panels, and chassis parts, thereby supporting fatigue life prediction, maintenance planning, and failure prevention.

Energy and Nuclear Systems

PFM helps to evaluate fractures in materials exposed to extreme conditions, such as turbine blades, nuclear reactor components, and pressure vessels. It captures ductile-to-brittle transitions at low temperatures, high-strain-rate impacts, and coupled thermomechanical loading, aiding in the design of safer and more resilient energy systems.

Microstructural and Material Design

By incorporating microstructural heterogeneity, phase-field models can guide the development of advanced materials with tailored fracture resistances. Applications include the prediction of crack propagation in metals with engineered grain structures, polymer composites, and additive-manufactured materials.

Fatigue and Dynamic Fracture

PFM has been extensively applied to simulate fatigue crack growth under cyclic loading and dynamic impact. It captures both high- and low-cycle fatigue behaviors, allowing the optimization of components subjected to repeated stresses, such as gears, rails, and biomedical implants.

Multiphysics Coupled Applications

PFM supports the modeling of coupled phenomena such as thermomechanical fracture, hydrogen embrittlement, and hydraulic fracturing in geomechanics. Its flexibility in integration with elasto-plasticity, thermal effects, and environmental factors makes it ideal for complex real-world applications. PFM provides engineers and researchers with a predictive framework for designing safer and more reliable materials and structures, accounting for both brittle and ductile fracture mechanisms under diverse and challenging loading conditions.

CONCLUSION

PFM has emerged as a robust and versatile computational framework for predicting brittle and ductile fractures under complex loading conditions. Regularizing sharp crack surfaces through a continuous scalar field eliminates the need for explicit crack tracking while naturally capturing crack initiation, propagation, branching, and coalescence. For brittle materials, the approach effectively models energy-driven crack growth, whereas extensions to ductile materials incorporate plastic deformation, strain hardening, and rate-dependent effects, enabling accurate prediction of ductile fracture and brittle-to-ductile transitions.

The adaptability of the methodology to multiaxial stresses, cyclic loading, dynamic impacts, and thermomechanical environments makes it highly relevant for engineering applications in the aerospace, automotive, structural, and energy sectors. Phase-field models allow the integration of microstructural heterogeneity, fatigue effects, and multiphysics couplings, providing a predictive tool for material design, failure analysis, and safety assessment.

© STM Journals 2025. All Rights Reserved

Despite its advantages, challenges remain, including the proper calibration of length-scale and degradation parameters, computational cost for large-scale 3D simulations, and validation against experimental data. Ongoing research focuses on improving numerical efficiency, extending the approach to complex multiphysics scenarios, and unifying brittle, ductile, and fatigue fracture modeling within a single framework.

Overall, PFM represents a transformative approach in fracture mechanics, offering enhanced predictive capability, flexibility, and reliability for analyzing material failure under complex real-world loading conditions, thus supporting safer and more efficient structural and material design.

REFERENCES

1. Zhang F, Huang W, Li X, Zhang S. A study on phase-field models for brittle fracture. Int J Numer Anal Model. 2022;19:1–38.
2. Dammaß F, Kalina KA, Ambati M, Kästner M. Phase-field modelling and analysis of rate-dependent fracture phenomena at finite deformation. Comput Mech. 2023;72:859–883. doi:10.1007/s00466-023-02310-1.
3. Huber W, Asle Zaeem MA. A mixed mode phase-field model of ductile fracture. J Mech Phys Solids. 2023;171:105123. doi:10.1016/j.jmps.2022.105123.
4. Liu B, Liu Z, Yang L. Accelerating fracture simulation with phase field methods based on Drucker–Prager criterion. Front Phys. 2023;11:1159566. doi:10.3389/fphy.2023.1159566.
5. Ben Said L, Hentati H, Turki M, Chabir A, Alharbi S, Haddar M. Efficient phase-field modeling of quasi-static and dynamic crack propagation under mechanical and thermal loadings. Mathematics. 2025;13:1742. doi:10.3390/math13111742.
6. Villalta G, Ferrer A, Otero F. Phase-field modeling of fracture via homogenization. Int J Fract. 2025;249:46. doi:10.1007/s10704-025-00861-3.
7. Sur AS, De Lorenzis L, Maurini C, Hopperstad OS. A variational phase-field model for ductile fracture depending on hydrostatic stresses. Meccanica. 2025;60:2151–2175. doi:10.1007/s11012-025-01971-x.
8. Dunić V, Gubeljak N, Živković M, Milovanović V, Jagarinec D, Djordjevic N. Experimental characterization and phase-field damage modeling of ductile fracture in AISI 316L. Metals. 2024;14:787. doi:10.3390/met14070787.
9. Kalina M, Schneider T, Waisman H, Kästner M. Phase-field models for ductile fatigue fracture. [Preprint]. 2024. arXiv:2411.05015. doi:10.48550/arXiv.2411.05015.
10. Diehl P, Lipton R, Wick T, Tyagi M. A comparative review of peridynamics and phase-field models for engineering fracture mechanics. Comput Mech. 2022;69:1259–1293. doi:10.1007/s00466-022-02147-0.
11. Xie C, He XK, Liu X, Ye JH, Chen JB. Phase-field modeling for anisotropic ductile damage of magnesium alloys at finite deformations. J Magnes Alloy. 2024;12:2967–2984. doi:10.1016/j.jma.2022.11.015.

© STM Journals 2025. All Rights Reserved