STM JOURNALS

Journal of
Nanoscience, Nanoengineering & Applications

ISSN: 2321-5194(Online)
ISSN: 2231-1777(Print)
Volume 16, Issue 2, 2026
May–August
DOI (Journal): 10.37591/JONSNEA

https://journals.stmjournals.com/jonsnea

Review JONSNEA

Bionanocomposites in Green Synthesis of Bioplastics – The Composite Materials of Future & Their Role in Circular Bio-Economy

Mukesh Chander[1], Prabhjit kaur[2], Rajbir Singh[2,Circular] *

Abstract

The pervasive use of petroleum-derived plastics has caused severe environmental pollution, accumulating in landfills and oceans while threatening human and animal health. This ecological crisis has accelerated an urgent transition toward biodegradable polymers within the circular bioeconomy. Bionanocomposites, comprising a biodegradable polymer matrix integrated with nanoscale fillers, successfully bridge the gap between high industrial performance and environmental responsibility. By incorporating advanced nanofillers, such as cellulose nanocrystals, chitin nanofibers, layered silicates (like montmorillonite), bio-graphene, and metallic or metal-oxide nanoparticles Ag, ZnO, TiO_2, these materials achieve enhanced mechanical strength, tailored stiffness, superior thermal stability, and optimized gas barrier properties. Furthermore, these ultra-low filler loadings minimize raw resource consumption while embedding active antimicrobial and antioxidant functionalities into the host matrix. Consequently, bionanocomposites are highly sought after for cutting-edge applications, including active and intelligent food packaging, agricultural films, protective coatings, tissue engineering scaffolds, and targeted drug-delivery systems. To minimize manufacturing footprints, sustainable, eco-friendly processing strategies – such as solvent-free melt extrusion, reactive extrusion, and bio-based compatibilizers – are employed. These techniques drastically reduce energy demands and hazardous chemical waste while allowing precise architectural control over the polymer. Ultimately, these innovations establish viable circular end-of-life pathways, including industrial composting and chemical recycling. Future research must focus on life-cycle optimization, standardizing characterization protocols, and advanced engineering of multifunctional bionanocomposites that simultaneously integrate active barrier control, antimicrobial protection, and real-time sensor capabilities.

Keywords: Biocomposites, bioplastic-nanomaterials, circular bio-economy, life cycle assessment, chemical recycling

***Author for Correspondence**
Rajbir Singh
E-mail:mukeshchander76@gmail.com

[1]Assistant Professor, Department of Biotechnology, Khalsa College, Amritsar, Punjab, India
[2]Assistant Professor, Department of Botany, Khalsa College, Amritsar, Punjab, India

Received Date: June 04, 2026
Accepted Date: June 19, 2026
Published Date: June 25, 2026

Citation: Mukesh Chander, Prabhjit Kaur, Rajbir Singh. Bionanocomposites in Green Synthesis of Bioplastics – The Composite Materials of Future & Their Role in Circular Bio-Economy. Journal of Nanoscience, Nanoengineering & Applications. 2026; 16(2): 70–82p.

INTRODUCTION

The contemporary materials science landscape is undergoing a profound paradigm shift, defined by an urgent transition from linear, fossil-dependent manufacturing models to a regenerative, circular bioeconomy [1, 2]. For over a century, the global industrial economy has operated under a "take-make-dispose" ethos reliant on petroleum-based synthetic polymers [1, 3]. While conventional plastics – like polyethylene, polypropylene, and polyethylene terephthalate – have provided unparalleled thermodynamic stability, mechanical resilience, and cost-effectiveness, their structural persistence has generated an unprecedented

© STM Journals 2026. All Rights Reserved

environmental crisis [2, 4, 5]. Global plastic production has surpassed hundreds of millions of metric tons annually, resulting in ubiquitous microplastic contamination across marine and terrestrial trophic levels, severe landfill congestion, and macro-scale ecological fragmentation (Figure 1) [1, 2, 6]. Concurrently, the petrochemical extraction and refining processes required to sustain conventional polymer production generate massive greenhouse gas emissions, fundamentally conflicting with international carbon neutrality targets and climate mitigation mandates [6].

To mitigate these ecological liabilities, early-generation bioplastics derived from renewable biomass, such as polylactic acid (PLA), polyhydroxyalkanoates (PHAs), starch, and cellulose derivatives, were introduced as potential sustainable alternatives [6–8]. However, the widespread industrial and commercial adoption of neat biopolymers remains constrained by severe, inherent material deficiencies. When compared directly to their petroleum-derived counterparts, pristine biopolymers consistently exhibit poor mechanical strength, brittle tensile behavior, low thermal stability, high moisture sensitivity, and inadequate gas and vapor barrier properties [1, 3, 9]. These performance deficits are particularly problematic in demanding sectors, such as food packaging, agricultural films, and biomedical devices, where stringent moisture regulation and oxygen barrier characteristics are mandatory to maintain structural integrity and shelf life. To transcend these physical boundaries, the convergence of nanotechnology and macromolecular polymer science has birthed an advanced class of hybrid systems: bionanocomposites synthesized through the integration of functional nanomaterials [4, 8, 10, 11]. These multiphase systems are formally defined as structural configurations where a continuous, bio-based, or biodegradable polymer matrix is reinforced by a secondary, discontinuously dispersed phase composed of advanced nanomaterials possessing at least one dimension below 100 nanometers. By deploying sustainable nanomaterials – such as cellulose nanocrystals (CNCs), chitin nano whiskers, montmorillonite nanoclays, graphene oxide nanomaterials, or biogenic metal nanoparticles – bionanocomposites bypass the historical trade-offs that have limited green material performance [3, 12–14]. The strategic selection of these specific nanomaterials allows engineering of the chemical interface to achieve structural properties that pristine polymers cannot match.

The core thermodynamic and mechanical advantages of these bionanocomposites lie in the spatial scale and dispersion of their internal nanomaterials. In traditional macromolecular composites, heavy filler volumes (often ranging between 10% and 40% by weight) are required to achieve tangible mechanical upgrades, which frequently compromise the density, flexibility, and processing mechanics of the parent polymer. Conversely, polymer systems reinforced with specialized nanomaterials trigger dramatic macro-scale property enhancements at ultra-low loading levels, typically between 1% and 5% by weight. This profound efficiency is directly attributed to the exceptionally high surface-area-to-volume ratio characteristic of engineered nanomaterials [6]. This vast interfacial surface area optimizes interfacial adhesion and builds extensive hydrogen bonding or covalent cross-linking networks between the incorporated nanomaterials and the surrounding host biopolymer matrix. Consequently, these structural parameters facilitate the formation of a percolated network of nanomaterials within the host polymer, enabling efficient stress transfer across the phase boundary, restricting the segmental mobility of the polymer chains, and constructing tortuous pathways that drastically slow down the diffusion of gas and water molecules through the matrix [13, 15, 16]. These tortuous pathways, induced directly by the geometry of the nanomaterials, effectively trap penetrant molecules and maximize barrier performance.

Beyond optimizing immediate physical properties, the production and sourcing of these nanomaterials serve as a vital vehicle for comprehensive waste valorization within a functional circular bioeconomy [17]. Rather than relying entirely on arable land and virgin crops for raw biopolymer extraction, modern synthesis pathways prioritize the extraction of bio-based nanomaterials from agro-industrial residues, lignocellulosic byproducts, and municipal food waste as primary feedstocks [9, 16]. By converting abundant organic secondary streams – such as waste straw, husks, and processing discards – into high-value crystalline nanomaterials or matrix pre-cursors, these processes effectively divert organic matter away from municipal landfills, lower methane outgassing during decomposition, and reduce structural reliance on virgin primary resources [17].

© STM Journals 2026. All Rights Reserved




Figure 1. Bionanocomposites for a circular economy – sustainable materials.

© STM Journals 2026. All Rights Reserved

Isolating nanomaterials from agricultural waste streams represents an eco-friendly blueprint for upcycling low-value biomass into high-performance industrial components. Importantly, these highly engineered polymer structures embedded with bio-based nanomaterials are strategically designed to satisfy sustainable end-of-life (EOL) scenarios [11]. Unlike conventional multi-material laminates that defy commercial sorting and recycling, composites integrated with biodegradable nanomaterials are tailored for seamless integration into industrial composting facilities, home biodegradation environments, and advanced enzymatic recycling systems [2, 8, 12]. Under controlled compost conditions, the embedded nanomaterials can accelerate the hydrolytic and microbial fragmentation of the hosting biopolymer matrix without introducing persistent chemical toxicities or heavy metal ecotoxicity into the surrounding soil [3]. Because these nanomaterials originate from natural organic templates, their environmental breakdown yields harmless, natural organic matter.

This holistic, multi-tiered approach aligns perfectly with modern global regulatory frameworks designed to phase out persistent single-use plastics. Specifically, the development of functional materials utilizing non-toxic nanomaterials directly satisfies the circularity criteria outlined in the European Green Deal and its corresponding Packaging and Packaging Waste Regulations, which mandate absolute climate neutrality and comprehensive material recyclability by mid-century [8, 14]. Concurrently, these bio-based innovations offer compliance mechanisms for the rapidly emerging Extended Producer Responsibility (EPR) mandates being enacted across Asia and North America. By shifting environmental and financial post-consumer liabilities back to manufacturers, EPR regulations incentivize the commercial integration of highly processable, non-toxic, and truly circular applications of green nanomaterials. In conclusion, this review systematically examines the synthesis pathways, processing mechanics, structure–property relationships, and ecological life-cycle metrics of next-generation composites utilizing structural nanomaterials. By analyzing the structural synergetic mechanics between green nanomaterials and biopolymer matrices, this text highlights the capacity of advanced nanomaterials to bridge the historic gap between industrial performance standards and global ecological equilibrium.

CLASSIFICATION AND PHYSICOCHEMICAL PROPERTIES OF BIOPOLYMER MATRICES

The performance of a bionanocomposite is fundamentally anchored in the chemical nature of its matrix. Biopolymers are generally categorized by their origin and production method, which dictates their thermal stability, crystallinity, and degradation profile.

Polylactic Acid (PLA) and Aliphatic Polyesters

Polylactic Acid (PLA) is the most commercially mature and extensively researched biopolymer. It is a linear thermoplastic polyester synthesized through the ring-opening polymerization (ROP) of lactide monomers, derived from the fermentation of starch-rich crops like corn and sugarcane. The properties of PLA are highly dependent on the stereochemical ratio of L-lactide and D-lactide isomers. High optical purity of the L-isomer results in a semi-crystalline material with high mechanical strength and a melting temperature [5, 13]. However, PLA exhibits inherent brittleness and a low glass transition temperature, which limits its use in high-temperature applications and durable goods. Bionanocomposite engineering seeks to broaden this processing window by introducing nanoclays or carbon nanotubes that act as nucleating agents, increasing the crystallization rate and improving the heat distortion temperature (HDT) [5, 6].

Polyhydroxyalkanoates (PHA) and Microbial Polyesters

Polyhydroxyalkanoates (PHAs) are a family of polyesters synthesized intracellularly by various bacteria as energy reserves under nutrient-limited conditions. The most common member, Poly(3-hydroxybutyrate) (PHB), is highly crystalline and exhibits mechanical properties like polypropylene [13–15]. PHAs are unique because they are truly biodegradable in both soil and marine environments, making them ideal for applications where plastic leakage into the ocean is a concern [8, 15]. Despite their environmental benefits, pure PHB is challenging to process due to its high crystallinity and a narrow thermal stability window; its degradation temperature is close to its melting point. This

© STM Journals 2026. All Rights Reserved

necessitates the development of PHB-based bionanocomposites, often incorporating bacterial cellulose (BC) nanofibers or nanoclays to enhance melt strength and reduce brittleness [15].

Polysaccharide-Based Matrices: Starch, Chitosan, and Cellulose

Polysaccharides are abundant, renewable, and cost-effective. Thermoplastic starch (TPS) is produced by disrupting the granular structure of native starch with heat and plasticizers like glycerol. While widely available, TPS is highly hydrophilic and suffers from "retrogradation," where the starch molecules reorganize over time, leading to embrittlement [3, 4]. Chitosan, obtained from the deacetylation of chitin found in crustacean shells, offers inherent antimicrobial properties and high chemical reactivity due to its primary amino groups. It is frequently used in biomedical and active food packaging [13, 16]. Cellulose-based matrices, including cellulose acetate and carboxymethyl cellulose (CMC), provide high transparency and mechanical stiffness, though they often require nanofiller reinforcement to achieve the barrier performance needed for long-term food preservation (Table 1) [4, 14].

Table 1. Comparative physicochemical and mechanical properties of biopolymer matrices.

Biopolymer matrix	Origin	Density	Tensile modulus	Elongation at break (%)
PLA	Corn/ Sugarcane	1.25–1.30	6.9–9.8	12–26
PHB	Bacteria	1.25	1.0–3.5	3–8
PHBV	Bacteria	1.24	0.8–2.0	5–50
TPS (Starch)	Potatoes/Corn	1.1–1.4	0.01–0.6	20–100+
Chitosan	Shellfish	1.35–1.40	1.5–3.0	5–25
Gelatin	Animal Collagen	1.30	0.3–2.5	10–60
Cellulose	Wood/Plants	1.50	100–150*	<5*

Protein-Based and Specialized Biopolymers

Proteins – like collagen, gelatin, and keratin – are utilized for their exceptional biocompatibility and cell-adhesion properties in tissue engineering [14, 17]. Gelatin, a hydrolyzed form of collagen, forms stable hydrogels that can be reinforced with chitin nanoparticles or nanocellulose to create scaffolds for bone reconstruction [4, 17]. Pullulan, a water-soluble polysaccharide produced by the fungus *Aureobasidium pullulans*, is emerging as a coating material due to its oxygen barrier properties and non-toxic nature [14].

DIMENSIONS AND MECHANISMS OF NANOSCALE REINFORCEMENTS

The efficacy of a bionanocomposite is determined by the dimensionality and surface chemistry of the nanofiller, which dictates the reinforcement mechanism and the formation of a "tortuous path" for permeants.

Zero-Dimensional (0D) Nanoparticles: Metal Oxides and Quantum Dots

Zero-dimensional nanofillers, such as silver, zinc oxide, and titanium dioxide, are primarily integrated for functional rather than structural roles. Their high surface-area-to-volume ratio enhances their chemical reactivity, making them potent antimicrobial agents and UV-blockers [4]. In food packaging, nanoparticles can photodegrade ethylene, extending the shelf life of climacteric fruits (Figure 2). In biomedical applications, nanoparticles are used in wound dressings to prevent bacterial colonization [4, 14].




Figure 2. Nanoparticle of zero-dimension order.

© STM Journals 2026. All Rights Reserved

One-Dimensional (1D) Nanofillers: Nanotubes and Nanofibers

One-dimensional reinforcements, including carbon nanotubes (CNTs) and cellulose nanocrystals (CNCs), provide exceptional longitudinal stiffness and strength. CNCs, isolated from wood pulp or bacterial cellulose, possess a high crystallinity and a tensile modulus exceeding [18–20]. When dispersed in a PLA matrix, CNCs facilitate stress transfer through hydrogen bonding between the hydroxyl groups of cellulose and the carbonyl groups of PLA (Figure 3). Bacterial cellulose (BC) nanofibers are particularly effective in reinforcing PHB, where they form a skeletal network that increases the storage modulus by up to 43% at high temperatures [15].




Figure 3. A nanoparticle of one-dimensional order.

Two-Dimensional (2D) Layered Silicates: The Clay Paradigm

Layered silicates, such as Montmorillonite (MMT) and Kaolinite, are the most widely used fillers due to their high aspect ratio and ability to create a "tortuous path" [3, 4, 13]. These nanoclays consist of stacked platelets about 1 nm thick. When integrated into a biopolymer, they can exist in three states:

- *Flocculated/Tactoid:* Platelets remain in stacks, offering minimal reinforcement.
- *Intercalated:* Polymer chains penetrate the interlayer space, increasing the spacing but maintaining the stack structure.
- *Exfoliated:* Individual platelets are completely dispersed throughout the matrix, maximizing surface area and barrier performance (Figure 4) [3, 4, 13].




Figure 4. Two-dimensional nanoparticles.

Exfoliated MMT is particularly effective in starch-based bionanocomposites, where it reduces water vapor permeability by creating a maze that gas molecules must navigate, effectively increasing the diffusion path length [3, 4].

Three-Dimensional (3D) and Hybrid Nanofillers

Three-dimensional nanofillers – like nanosized calcium carbonate and silica – are used to enhance the stiffness and thermal stability of bionanocomposites while maintaining cost-effectiveness [6, 9]. Hybrid systems, combining two or more nanofillers (e.g., CNC and MMT), are being explored to achieve synergistic effects, such as simultaneous improvements, in mechanical strength and antimicrobial activity [21, 22].

GREEN SYNTHESIS METHODOLOGIES AND FABRICATION TECHNOLOGIES

Green synthesis prioritizes the elimination of hazardous solvents, the reduction of energy consumption, and the use of renewable precursors.

Mechanochemical Synthesis: High-Energy Ball Milling

Mechanical milling (MM) is a solvent-free "solid-state mixing" technique that achieves homogeneous dispersion through high-energy impact and shear. In planetary ball mills, the grinding

© STM Journals 2026. All Rights Reserved

media (steel or ceramic balls) transfer kinetic energy to the polymer–filler mixture, facilitating the intercalation and exfoliation of layered silicates [4, 23, 24]. This process can be conducted at room temperature, which is advantageous for thermally sensitive biopolymers like starch. Hydrophilic ball milling has been shown to successfully exfoliate MMT clay into oxidized starch, resulting in a substantially higher breaking strength and fracture work compared to native starch [4].

Microwave and Ultrasound-Assisted Synthesis

Microwave irradiation offers rapid and selective heating by directly interacting with the polar molecules of the reactants. This technology significantly reduces the reaction time for synthesizing metal nanoparticles within biopolymer matrices, often using water as the solvent [25–27]. Unlike conventional heating, which relies on conduction, microwave energy causes molecular oscillation throughout the bulk of the material, leading to uniform temperatures and improved yields [25, 26].

Ultrasound-assisted processing utilizes acoustic cavitation to break down nanoparticle aggregates and accelerate polymerization reactions [25, 26]. In the fabrication of starch/nanofiber composites, ultrasonic vibration has been proven to enhance properties by promoting the deep penetration of fibers into the polymer matrix, thereby reducing the required loading content [4].

Biological Synthesis (Biosynthesis)

Biosynthesis leverages the metabolic pathways of microorganisms (bacteria, fungi, yeast) and plant extracts to produce nanoparticles. Plant extracts are particularly favored as they contain polyphenols and flavonoids that act as natural reducing and capping agents, producing stable nanoparticles under ambient conditions (Table 2) [28, 29]. Fungi can secrete large amounts of enzymes that catalyze the reduction of metal ions, providing a scalable and eco-friendly route for producing antimicrobial fillers for food packaging [28].

Table 2. Comparison of green fabrication techniques for bionanocomposites.

Fabrication method	Primary mechanism	Solvent usage	Energy efficiency	Scalability	Key advantage
Ball Milling	Mechanical shear/impact	None	High	Moderate	Solvent-free exfoliation.
Microwave	Dielectric heating	Water/Green	Very High	High	Ultra-fast reaction times.
Ultrasound	Acoustic cavitation	Water/Green	High	Moderate	Excellent de-agglomeration.
Biosynthesis	Microbial/Plant reduction	Aqueous	Very High	High	Low toxicity, high safety.
Melt Extrusion	Thermal/Mechanical shear	None	Moderate	Very High	Compatible with industry.
Solution Casting	Evaporation/Gelling	High (Bio-based)	Low	Moderate	High dispersion quality.

PERFORMANCE ENGINEERING AND INTERFACIAL OPTIMIZATION

The interface between the nanofiller and the biopolymer matrix is the critical region where stress is transferred and permeants are blocked.

Surface Modification and Functionalization

Many biopolymers are hydrophilic (e.g., starch, chitosan), while others are relatively hydrophobic (e.g., PLA, PHB). This mismatch can lead to poor interfacial adhesion and filler aggregation. Surface modification techniques are employed to tailor the surface energy of the fillers.

- *Anhydride Modification:* Treating biofibers or nanocellulose with propionic or succinic anhydride increases their hydrophobicity, improving their compatibility with hydrophobic matrices like vinyl ester or PLA [30].

© STM Journals 2026. All Rights Reserved

- *Silanization:* The use of silane coupling agents creates chemical bridges between inorganic fillers (like nanoclays) and organic polymers.
- *Plasma Treatment:* Atmospheric or argon plasma treatment can functionalize the surface of biopolymers, increase surface roughness, and induce chemical crosslinking. For PHB/bacterial cellulose nanocomposites, plasma treatment has been shown to increase the storage modulus by 19% at room temperature and enhance antimicrobial activity against *E. coli* by 63% [15].

Rheological and Processing Behavior

The introduction of nanofillers significantly alters the melt rheology of biopolymers. In bionanocomposites based on Bioflex (BF), the addition of organ-modified nanoclays induces an apparent yield stress at low frequencies, indicating the formation of a filler network that restricts macromolecular dynamics [6]. Conversely, traditional plastics – like HDPE – are almost unaffected by the same fillers due to a lack of specific interactions [6]. These rheological changes are critical for processes, like pipe extrusion and blow molding, where melt strength and deformability are essential for maintaining structural integrity [6]. The quantification of property improvements is essential for evaluating the potential of bionanocomposites to replace petroleum plastics. The addition of only 1% to 2% bacterial cellulose to PHB can result in a 21% increase in tensile strength (Table 3). In starch-based systems, MMT reinforcement at 5% wt can reduce water vapor permeability by 50% compared to native starch [3, 4].

Table 3. Summary of mechanical and antimicrobial enhancements in bionanocomposites.

Matrix	Nanoreinforcement	Loading	Property improved	Result
PLA	CNC	3–5 wt%	Tensile Modulus	58% increase [18].
PLA	CNC	3–5 wt%	Tensile Strength	87% increase [18].
PLA	MMT Clay	5 vol%	Storage Modulus	Significant improvement [5].
PHB	BC Nanofibers	2 wt%	Storage Modulus	43% increase at [15].
Starch	MMT Clay	5 wt%	Breaking Strength	Substantial enhancement [4].
Chitosan		1 wt%	Antimicrobial ()	Synergistic inactivation [4].
Guar Gum	Alloy NPs	2 wt%	Antimicrobial ()	Increased activity with conc [4].

Role in the Circular Bio-Economy: Waste to Worth

A circular bioeconomy focuses on establishing regenerative systems that minimize waste and keep resources in continuous circulation.

Valorization of Agro-Industrial and Food Waste

Bionanocomposites promote sustainability by utilizing recycled agricultural and industrial waste, such as rice husk ash, lignin, and waste glass powder [8, 19]. Approximately 1.3 billion tons of food waste (FW) are generated annually, which, if improperly managed, releases toxic gases and contaminates groundwater. Converting this FW into bioplastics and bionanocomposites provides a "second life" for these materials (Table 4). Cellulose and lignocellulosic fractions from food waste are increasingly being converted into high-value biopolymers – like PLA and PHA – through microbial fermentation.

Table 4. Waste Feedstocks and resulting bionanocomposite components.

Waste feedstock	Recovered component	Targeted bionanocomposite	Circular economy benefit
Rice Husk	Silica/Carbon Ash	Reinforced PLA/PHA	Waste reduction, cheap filler.
Crustacean Shells	Chitin/Chitosan	Antimicrobial Packaging	Valorization of seafood waste.
Sugarcane Bagasse	Cellulose Nanocrystals	Structural Bio-composites	Non-food biomass utilization.
Food Scraps	Fermentable Sugars	PHA/PHB Matrix	GHG emission reduction.
Waste Glass	Nanopowder	Thermal Insulation	Circular material loop.

© STM Journals 2026. All Rights Reserved

Life Cycle Assessment (LCA) and Environmental Footprint

LCA is a comprehensive tool used to quantify the environmental impact of bionanocomposites from "cradle to grave." Studies indicate that bio-based plastics generally have a lower carbon footprint than fossil-based plastics (Table 5). For instance, the use of starch in bioplastic production can reduce GHG emissions by up to 80% and non-renewable energy usage by up to 60%. Utilizing Bio-PE leads to GHG emissions of approximately, which is 140% lower than petrochemical PE. However, LCAs also highlight trade-offs. The production of bioplastics can increase eutrophication potential by up to 400% due to the intensive use of fertilizers and pesticides in biomass cultivation [31, 32]. The use of waste residues instead of "virgin" starch can mitigate these impacts, reducing land use by up to 60% and eutrophication potential by up to 40% [31].

Table 5. Quantitative LCA data: Bionanocomposites vs. traditional plastics.

Material comparison	Category	Quantitative difference	Context
PLA vs. Conventional	Energy Usage	66% Savings	Corn-based feedstock [31].
PLA vs. Conventional	GHG Emissions	25% Reduction	Corn-based feedstock [31].
Starch vs. Petrochemical	GHG Emissions	80% Reduction	Waste-derived starch [31].
Bio-PE vs. Fossil PE	GHG Emissions	140% Lower	[31].
Compostable vs. LDPE	Carbon Emissions	79% Lower	Including Biogenic Carbon [33].
Bio-based Epoxy	Emissions	Significant Reduction	For ammonia tankers [34].

The sustainability of bionanocomposites depends on effective management at the end of their service life.

Biodegradation and Industrial Composting

Biodegradation is the enzymatic scission of polymer chains by microorganisms. Composting is a form of biodegradation that yields water and humus, but it requires specific conditions of pH, humidity, and oxygenation [5, 9]. While many bionanocomposites are compostable, the presence of certain nanofillers can either accelerate or retard this process, depending on their influence on crystallinity and water absorption.

Enzymatic and Chemical Upcycling

Enzymatic recycling is an emerging biotechnology that utilizes engineered enzymes to depolymerize plastics into their original monomers under mild conditions (), often without the need for solvents [10]. This method is highly specific and can handle colored or soiled plastics, allowing for the infinite reuse of materials in a closed-loop system [33, 34]. Chemical upcycling transforms waste plastics into high-value carbon-based nanomaterials (CNMs), such as graphene and carbon nanotubes, through processes like pyrolysis, flash joule heating (FJH), and catalytic degradation (Table 6). A Chemical Upcycling Framework (CUF) tested in the UK, Netherlands, and Japan demonstrated a 70% to 85% conversion efficiency for multilayer plastics, increasing material value by 60% [35].

Table 6. Comparison of plastic recycling and upcycling pathways.

Pathway	Mechanism	End product	Environmental impact
Mechanical Recycling	Grinding/Remelting	Lower-quality plastic	Low energy, quality loss.
Chemical Recycling	Solvolysis/Pyrolysis	Monomers/Fuels	High energy, true circularity.
Enzymatic Recycling	Biocatalysis	Pure Monomers	Mild conditions, high specificity.
Carbon Upcycling	Thermal decomp. /CVD	Graphene/CNTs	High value, carbon storage.
Composting	Biodegradation	, Water, Humus	Returns carbon to soil.

Diverse Applications of Bionanocomposites

Bionanocomposites are transitioning from laboratory research to industrial and medical applications.

© STM Journals 2026. All Rights Reserved

Active and Intelligent Food Packaging

The high surface-to-volume ratio of nanofillers makes bionanocomposites ideal for "active" packaging. By integrating antimicrobial agents, like silver or zinc oxide, these materials can inhibit the growth of pathogens like *E. coli* and *S. aureus* [4]. Intelligent packaging systems incorporate bionanocomposite sensors that provide real-time information on food safety, such as color-changing indicators, for temperature fluctuations or freshness levels (Table 7).

Table 7. Specific food packaging innovations.

Application type	Nanocomposite system	Targeted food	Function
Active Packaging	Chitosan +	Climacteric Fruits	Ethylene photodegradation.
Active Packaging	Starch + Nisin/Clay	Meat/Dairy	Inhibits *L. monocytogenes*.
Intelligent Pkg	CMC + Silver NPs	Temperature sensitive	Color-based TTI indicator.
Edible Coatings	Bionanocomposite film	Fruits/Veg	Disease management.
High Barrier Pkg	PLA + Nanoclay	Liquids/Gases	Reduces and moisture perm.

Biomedical Applications: From Wound Healing to Tissue Scaffolds

The biocompatibility and tunable mechanical properties of bionanocomposites make them gamechangers in the medical field. Chitosan and alginate-based nanocomposites are used in drug delivery systems to ensure the controlled release of therapeutics [14, 17]. In tissue engineering, scaffolds reinforced with hydroxyapatite or nanoclays mimic the extracellular matrix (ECM), promoting cell growth and bone regeneration [3, 14, 17]. Emerging "smart" bionanocomposites are responsive to stimuli, like pH or temperature, which is ideal for targeted cancer drug delivery [17, 20].

Industrial and Engineering Applications

Bionanocomposites are increasingly applied in the automotive and construction sectors due to their lightweight and durable nature [22]. In the automotive industry, they are used for vehicle body panels, interior components, and battery housings to achieve energy savings. Hybrid composites of basalt fiber and bio-epoxy have shown potential for semi-structural marine applications, offering high resistance to seawater degradation [22]. In agriculture, Bioflex-based nanocomposite pipes fulfil the requirements for irrigation systems, providing a bio-based alternative to standard HDPE pipes [36–38].

Global Market Trends and Regulatory Dynamics (2025–2032)

The adoption of bionanocomposites is being accelerated by stringent global environmental regulations. Europe's Packaging and Packaging Waste Regulation (PPWR), entering into force in February 2025, harmonizes measures for manufacturing, recycling, and reuse, strengthening the market for secondary raw materials [37–39]. The EU aims for a circularity rate of 24% by 2030, a goal that favors the use of bio-based and recyclable bionanocomposites [12]. China has set a definitive 2025 deadline for nationwide bans on non-degradable plastic packaging bags and tape in the e-commerce and logistics sectors. Major courier companies are already transitioning to degradable and paper-based cushioning materials to avoid fines of up to RMB 20,000. Japan and South Korea are moving toward mandating the use of recycled plastic, with South Korea targeting a 10% share of recycled content in packaging by 2026. Vietnam and Indonesia have also established 2026 as a hard deadline for banning non-biodegradable plastic bags and single-use items in the retail and tourism sectors (Table 8).

Table 8. Global circular economy policy timelines.

Region	Year	Regulation/milestone	Specific impact
China	2025	National Plastic Ban (Hard Deadline)	Full phase-out of non-degradable bags.
EU	2025	PPWR Enforcement	Mandatory recyclability & reuse rules.
S. Korea	2026	Recycled Plastic Mandate	10% target for recycled content.
Vietnam	2026	Import/Production Ban	Ban on non-biodegradable plastic bags.
Indonesia	2026	Comprehensive Plastic Ban	End of single-use plastic usage.
EU	2030	Circular Economy Act Targets	Goal of 24% circularity rate.
USA (CA)	2032	SB 54	25% reduction in plastic packaging.

© STM Journals 2026. All Rights Reserved

FUTURE OUTLOOK AND STRATEGIC CONCLUSIONS

Bionanocomposites stand at the forefront of the material revolution, offering a technically viable and environmentally superior alternative to petroleum-based plastics. The transition from fundamental research to industrial dominance is being driven by innovations in green synthesis, such as ball milling and enzymatic recycling, and by the integration of bionanocomposites into a circular bioeconomy through waste valorization. Despite challenges related to production costs and technical complexity, the synergy between materials science and biotechnology is creating a roadmap for a carbon–neutral future. The use of machine learning (ML) and predictive modeling (e.g., Random Forest algorithms) is further accelerating the development of high-performance composites, allowing researchers to optimize properties without extensive trial-and-error. As global regulations tighten and consumer demand for sustainable products grows, bionanocomposites will play an indispensable role in securing a circular, bio-based economy for future generations.

The convergence of nanotechnology, green chemistry, and circular economy principles ensures that bionanocomposites are not merely the "materials of the future" but the necessary foundation for a sustainable present. Strategic investments in local waste collection, biorefinery infrastructure, and advanced recycling technologies will be the key drivers in scaling these innovations to meet global sustainability targets by 2030 and beyond.

REFERENCES

1. Mori R. Replacing all petroleum-based chemical products with natural biomass-based chemical products: A tutorial review. RSC Sustain. 2023;1(2):179–212. doi: 10.1039/d2su00014h.
2. Abu-Zurayk R, Khalaf A, Alnairat N, Waleed H, Bozeya A, Abu-Dalo D, et al. Green polymer nanocomposites: Bridging material innovation with sustainable industrial practices. Front Mater. 2025;12:1701086.
3. Goodman BA. Utilization of waste straw and husks from rice production: A review. J Bioresour Bioprod. 2020;5(3):143–62. doi: 10.1016/j.jobab.2020.07.001.
4. Kovacevic Z, Flincec Grgac S, Bischof S. Progress in biodegradable flame retardant nano-biocomposites. Polymers. 2021;13:741. doi: 10.3390/polym13050741.
5. Krystyjan M, Khachatryan G, Khachatryan K, Konieczna-Molenda A, Grzesiakowska A, Kuchta-Gładysz M, et al. The functional and application possibilities of starch/chitosan polymer composites modified by graphene oxide. Int J Mol Sci. 2022;23(11):5956. doi: 10.3390/ijms23115956.
6. Bhat AH, Khan I, Amil Usmani M, Rather JA. Bioplastics and bionanocomposites based on nanoclays and other nanofillers. In: Nanoclay reinforced polymer composites: Nanocomposites and bionanocomposites. Singapore: Springer Singapore; 2016. p.115–39. doi: 10.1007/978-981-10-1953-1_5.
7. Deffo G, Temgoua RC, Njanja E, Puzari P. Bionanocomposite materials for electroanalytical applications: Current status and future challenges. Nanoscale Adv. 2024;6(19):4736–50. doi: 10.1039/D3NA01111A.
8. Chander M, Lovejot. Applications of bionanocomposites in healing & treatment of tendon & ligament injuries. Int J Compos Constituent Mater. 2026;12(1).
9. Bharathi VS, Jayas DS. Evolution of bionanocomposites: Innovations and applications in food packaging. Foods. 2024;13(23):3787. doi: 10.3390/foods13233787.
10. Sinha Ray S. Polylactide-based bionanocomposites: A promising class of hybrid materials. Acc Chem Res. 2012;45(10):1710–20. doi: 10.1021/ar3000376.
11. Botta L, La Mantia FP, Mistretta MC, Oliveri A, Arrigo R, Malucelli G. Structure-property relationships in bionanocomposites for pipe extrusion applications. Polymers. 2021;13(5):782. doi: 10.3390/polym13050782.
12. Vatieri C, Cirillo T, Esposito F. Waste to worth: Bioplastic synthesis from lignocellulosic food waste in the age of the circular bioeconomy. Front Sustain Food Syst. 2025;9:1698348. doi: 10.3389/fsufs.2025.1698348.
13. Chander M, Arora DS. Biodegradation of a dye by different white-rot fungi on a novel agro residue-based medium. Lignocellulose. 2014;3(1):37–50. doi: 10.13140/RG.2.2.34047.83368.

© STM Journals 2026. All Rights Reserved

14. Rosenboom JG, Langer R, Traverso G. Bioplastics for a circular economy. Nat Rev Mater. 2022;7(2):117–37. doi: 10.1038/s41578-021-00407-8.
15. Liu X, Park H, Ackermann YS, Avérous L, Ballerstedt H, Besenmatter W, et al. Exploring biotechnology for plastic recycling, degradation and upcycling for a sustainable future. Biotechnol Adv. 2025;81:108544. doi: 10.1016/j.biotechadv.2025.108544.
16. Wani SD, Mundada AS. A review: Emerging trends in bionanocomposites. Int J Pharm Res Technol. 2021;11(1):1–8. doi: 10.31838/ijprt/11.01.01.
17. Nandhini J, Karthikeyan E, Rajeshkumar S. Eco-friendly bio-nanocomposites: Pioneering sustainable biomedical advancements in engineering. Discover Nano. 2024;19(1):86. doi: 10.1186/s11671-024-04007-7.
18. Panaitescu DM, Ionita ER, Nicolae CA, Gabor AR, Ionita MD, Trusca R, et al. Poly(3-hydroxybutyrate) modified by nanocellulose and plasma treatment for packaging applications. Polymers. 2018;10(11):1249. doi: 10.3390/polym10111249.
19. Pires JR, Rodrigues C, Coelhoso I, Fernando AL, Souza VG. Current applications of bionanocomposites in food processing and packaging. Polymers. 2023;15(10):2336. doi: 10.3390/polym15102336.
20. Chander DM, Kumar DR, Salwan R. The synthesis of medicinally important pharma molecules from carbohydrates building blocks. Int J Novel Res Dev. 2023;8(5):e133–e148. Available from: https://ijnrd.org/viewpaperforall.php?paper=IJNRD2305414
21. Arora B, Bhatia R, Attri P. Bionanocomposites: Green materials for a sustainable future. In: New polymer nanocomposites for environmental remediation. Elsevier; 2018. p.699–712. doi: 10.1016/B978-0-12-811033-1.00027-5.
22. Abu-Zurayk R, Khalaf A, Alnairat N, Waleed H, Bozeya A, Abu-Dalo D, et al. Green polymer nanocomposites: Bridging material innovation with sustainable industrial practices. Front Mater. 2025;12:1701086. doi: 10.3389/fmats.2025.1701086.
23. Rawat S, Phogat P, Sharma S, Jha R, Singh S. Smart and adaptive bionanocomposite materials processing and fabrication. In: Advanced bionanocomposite materials: Innovations for sustainable development. Singapore: Springer Nature Singapore; 2025. p.125–79. doi: 10.1007/978-981-96-8225-6_4.
24. Yadav K, Dutta K, Poudel R, Karak N. Biocomposites for automotive applications. In: Advances in biocomposites and their applications. Woodhead Publishing; 2024. p.257–84. doi: 10.1016/B978-0-443-19074-2.00009-5.
25. Kharissova OV, Kharisov BI, González CM, Méndez YP, López I. Greener synthesis of chemical compounds and materials. R Soc Open Sci. 2019;6(11):191378. doi: 10.1098/rsos.191378.
26. Mohamed AA. Synthesis of nanomaterials under microwave and ultrasound irradiation. In: Green chemical synthesis with microwaves and ultrasound. 2024. p.235–48. doi: 10.1002/9783527844494.ch9.
27. Mohamed AA. Synthesis of nanomaterials under microwave and ultrasound irradiation. Green Chem Synth Microw Ultrasound. 2024. p.235–48. doi: 10.3390/c13111576.
28. Rizal S, HPS AK, Mistar EM, Olaiya NG, Muksin U, Marwan M, et al. Functional properties of kenaf bast fibre anhydride modification enhancement with bionanocarbon in polymer nanobiocomposites. Polymers. 2021;13(23):4211. doi: 10.3390/polym13234211.
29. Xia L, Gui T, Wang J, Tian H, Wang Y, Ning L, et al. Bio-based coatings: Progress, challenges and future perspectives. Polymers. 2025;17(24):3266. doi: 10.3390/poly17053266.
30. Chander M. Fungal-derived nutraceuticals & bioactive compounds with physiotherapeutic and health-promoting properties: A comprehensive review. Int J Fungi. 2025;2(2):1–9. doi: 10.37591/IJF.v02i02.228797.
31. Abdelfatah AM, Hosny M, Elbay AS, El-Maghrabi N, Fawzy M. From waste to worth: Upcycling plastic into high-value carbon-based nanomaterials. Polymers. 2024;17(1):63. Available from: https://www.researchgate.net/publication/387645615
32. Xu J, Zhang J. Upcycling of waste plastics into value-added chemicals. Sci Energy Environ. 2025;2(1):4. doi: 10.53941/see.2025.100004.

© STM Journals 2026. All Rights Reserved

33. Chander M. Biocomposites: Use of lignin as a core material in synthesis of various industrially important biomaterials. Int J Adv Eng Manag. 2021;3(8):593–602. doi: 10.35629/5252-0308593602.
34. Bano A, Gupta A, Prusty MR, Kumar M. Elicitation of fruit fungi infection and its protective response to improve the postharvest quality of fruits. Stresses. 2023;3(1):231–55. doi: 10.3390/stresses3010018.
35. Barbhuiya RI, Tinoco NN, Ramalingam S, Elsayed A, Subramanian J, Routray W, et al. A review of nanoparticle synthesis and application in the suppression of diseases in fruits and vegetables. Crit Rev Food Sci Nutr. 2024;64(14):4477–99. doi: 10.1080/10408398.2022.2142511.
36. Sánchez-Silva JM, López-García UM, Gutierrez-Martinez P, Flores-Ramírez AY, Ramos-Bell S, Moreno-Hernández C, et al. Bionanocomposite coating film technologies for disease management in fruits and vegetables. Horticulturae. 2025;11(7):832. doi: 10.3390/horticulturae11070832.
37. Sánchez-Silva JM, López-García UM, Gutierrez-Martinez P, Flores-Ramírez AY, Ramos-Bell S, Moreno-Hernández C, et al. Bionanocomposite coating film technologies for disease management in fruits and vegetables. Horticulturae. 2025;11(7):832. doi: 10.1016/j.fpsl.2022.100877.
38. Su G, Lin Y, Wang C, Lu J, Liu Z, He Z, et al. Expansin SlExp1 and endoglucanase SlCel2 synergistically promote fruit softening and cell wall disassembly in tomato. Plant Cell. 2024;36(3):709–26. doi: 10.1093/plcell/koad291.
39. Shahbazi F, Shahbazi S, Nadimi M, Paliwal J. Losses in agricultural produce: A review of causes and solutions, with a specific focus on grain crops. J Stored Prod Res. 2025;111:102547. doi: 10.1016/j.jspr.2025.102547.

© STM Journals 2026. All Rights Reserved