

Role of Supplementary Cementitious Materials in Enhancing Strength and Workability of Green Concrete

Parul Sharma*

Abstract

This collective review of ten seminal papers on green concrete highlights the growing emphasis on sustainable construction practices through the use of recycled materials, industrial by-products, and supplementary cementitious materials (SCMs). The studies consistently demonstrate that green concrete can significantly reduce carbon emissions, enhance durability, and maintain structural integrity comparable to conventional mixes. Experimental investigations confirm the viability of incorporating fly ash, silica fume, slag, quarry dust, and recycled concrete aggregates (RCA), with most mixes meeting or exceeding performance benchmarks in terms of compressive strength, workability, and long-term durability. Literature reviews and case studies further validate the environmental and economic benefits of green concrete, supporting its adoption in infrastructure projects and non-structural applications. Collectively, these papers underscore the potential of green concrete to transform the construction industry by aligning engineering performance with ecological responsibility. The reviewed studies investigate the use of materials such as fly ash, silica fume, ground granulated blast furnace slag (GGBS), quarry dust, RCA, and other waste-derived constituents as partial replacements for cement and natural aggregates. Experimental findings consistently indicate that green concrete can achieve mechanical and durability properties comparable to or better than those of conventional concrete. Most studies reported satisfactory compressive strength, improved resistance to chemical attacks, enhanced durability, and acceptable workability characteristics. Furthermore, the incorporation of waste materials contributes to effective waste management and conservation of natural resources. In addition to laboratory investigations, several literature reviews and case studies examined the practical implementation of green concrete in construction projects. These studies highlighted substantial environmental benefits, including reduced carbon footprint, lower energy consumption, and decreased landfill waste, along with potential economic advantages through material cost savings. The collective findings demonstrate that green concrete is a technically feasible, environmentally responsible, and economically viable construction material. Overall, this review underscores the transformative potential of green concrete in promoting sustainable infrastructure development and advancing the construction industry's transition toward greener and more resource-efficient practices.

*Author for Correspondence

Parul Sharma

E-mail: 2022pceceparul012@poornima.org

Student, Department of Civil, Poomima College of Engineering, ISI-6, RIICO Institutional Area, Sitapura, Jaipur, Rajasthan, India

Received Date: April 20, 2026

Accepted Date: June 09, 2026

Published Date: June 12, 2026

Citation: Parul Sharma. Role of Supplementary Cementitious Materials in Enhancing Strength and Workability of Green Concrete. Journal of Construction Engineering, Technology & Management. 2026; 16(2): 16–20p.

Keywords: Green concrete, sustainability, recycled materials, durability, supplementary cementitious materials (SCMs)

INTRODUCTION

Concrete, the most widely used construction material, has long been criticized for its environmental burden, particularly the high CO₂ emissions associated with cement production. The first highlighted the urgent need to “green” the concrete industry, advocating performance-based

specifications and the use of SCMs, such as fly ash, slag, and silica fume, to reduce clinker consumption and extend service life. Building on this foundation, sustainability pathways in concrete construction show that systematic material substitution and standardized sustainability metrics can achieve significant emission reductions without compromising strength. The utilization of industrial and agricultural waste, including foundry sand, bottom ash, and rice husk ash, as partial replacements for cement and fine aggregates, demonstrates their potential to improve durability while supporting waste management [1–3].

Recycled concrete aggregates (RCA) showed that demolition waste could be reused in structural concrete when strict quality controls, such as pre-soaking and grading, were applied, although workability and modulus reductions were noted at higher replacement levels. The performance of fly ash concrete confirmed improved workability and long-term strength but acknowledged early-age strength trade-offs. Experimental validation of green mixes combining RCA and fly ash proved that optimized blends can meet target strengths and workable slumps under practical conditions. Sustainable practices, synthesizing case studies, and emphasizing lifecycle cost-effectiveness and alignment with certification frameworks [4–7].

The role of RCA in sustainable construction was highlighted, emphasizing its contribution to the circular economy by diverting demolition waste from landfills while stressing the importance of source control and mix design adjustments. The concept of high-performance green concrete was demonstrated, showing that silica fume and slag can produce dense and durable mixes with superior resistance to chloride and sulfate attacks, making them suitable for marine and industrial environments. This study bridges research and practice by documenting successful field applications of green concrete in infrastructure projects and advocating its integration into building codes and procurement policies for mainstream adoption.

METHODOLOGY: STRUCTURE OF THE REVIEWS

This study adopted an experimental and analytical approach to evaluate the performance of green concrete. Various SCMs, such as fly ash, silica fume, slag, and quarry dust, along with RCA, were incorporated into concrete mixes. Standard mix designs were prepared with controlled water-to-binder ratios and compared with conventional concrete as a baseline.

Fresh properties such as slump, workability, and setting time were measured, while hardened properties including compressive strength, flexural strength, and durability were tested at different curing ages. The environmental performance was assessed through a life cycle analysis (LCA) to quantify CO₂ reduction and waste utilization. Literature reviews and case studies validated the laboratory findings, confirming the feasibility of green concrete in both structural and non-structural applications [8–9].

LITERATURE REVIEW AND PERFORMANCE CHARACTERISTICS

The literature on green concrete consistently highlights the role of core materials, such as fly ash, slag, and silica fume (SCMs), which reduce clinker content and embodied CO₂ while simultaneously improving long-term performance. RCA are feasible when appropriate processing and mix optimization are applied, and waste-derived fines, such as quarry dust, can partially replace sand or cement, provided that grading and reactivity are carefully controlled. The methodologies across the reviewed studies typically involved iterative mix design adjustments—varying water-to-cement ratios, binder replacement levels, and superplasticizer dosages—followed by mechanical testing at multiple ages to assess compressive, tensile, and flexural strength. Durability evaluations are comprehensive, including rapid chloride permeability tests (RCPT), sorptivity, permeability, and resistance to sulfate or acid attack, while fresh-state metrics such as slump, setting time, and rheology are also measured. Lifecycle assessments and case studies further corroborate the environmental benefits and real-world feasibility of these approaches.

Converging evidence from the literature indicates that hybrid SCM blends outperform single additions, particularly in terms of reducing permeability and enhancing chemical resistance. The negative effects of RCA on workability and stiffness are manageable through pre-soaking, refined grading, and admixture use, whereas early-age strength dips associated with high fly ash content can be mitigated by curing strategies and blended binders. Aggregated performance characteristics show that the compressive strength in SCM mixes matches or exceeds that of conventional concrete at 28–90 d, with slag and silica fume providing notable improvements, while fly ash may reduce early strength but converges later. Optimized RCA mixes achieve acceptable strengths for non-structural and selected structural applications. Durability is significantly enhanced, with silica fume and slag reducing permeability and chloride ingress, and hybrid SCM systems improving the resistance to sulfate and acid attack. Workability trends reveal that fly ash generally improves the slump and extends the setting time, whereas RCA lowers the slump owing to higher absorption, which can be balanced with admixtures and adjusted grading. Tensile, flexural, and modulus values show small to moderate gains with high-performance SCMs, while RCA may slightly reduce these properties owing to interfacial transition zone (ITZ) effects, although quality control mitigates such drawbacks.

From a sustainability perspective, the findings are clear: clinker substitution and recycled content deliver substantial CO₂ reductions, landfill diversion, and a reduced demand for virgin aggregates. Case studies confirm cost-effectiveness at scale, particularly when SCMs are locally available. Practical takeaways emphasize the importance of strategically blending SCMs, such as pairing fly ash with slag or silica fume, to achieve durability without excessive early-age penalties. The quality of RCA must be controlled through pre-soaking, limiting weakly adhered mortar, and refining grading, while durability should be specified in performance-based terms such as RCPT values. Curing discipline is critical, as extended curing unlocks the long-term mechanical and durability gains of high-SCM mixes. Finally, documenting impacts through quantified LCA metrics, including CO₂ reduction and waste diversion, is essential to support procurement decisions and policy adoption.

INNOVATIVE APPLICATIONS AND SUSTAINABILITY

Green concrete has demonstrated remarkable feasibility in various infrastructure projects, including bridges, pavements, and housing, where durability and a reduced carbon footprint are critical requirements. In high-performance structures such as marine facilities and high-rise buildings, mixes rich in SCMs, such as slag and silica fume, have been successfully applied, offering enhanced chemical resistance and superior mechanical strength compared to conventional concrete. A major contribution of green concrete lies in its ability to utilize industrial by-products such as fly ash, quarry dust, and slag, along with RCA, thereby reducing the burden on landfills and lowering the demand for virgin raw materials. Researchers have also highlighted the effectiveness of hybrid blends that combine SCMs with RCA, which balance mechanical strength, workability, and durability, making them suitable for real-world applications where performance and sustainability must coexist. Beyond structural applications, studies suggest that green concrete can be adapted for smart building purposes, offering improved thermal insulation and acoustic performance, which contribute to sustainable architecture. Policy-driven adoption has played a significant role in mainstreaming this innovation, with case studies documenting successful implementation in public infrastructure projects supported by sustainability mandates and green building certifications. Collectively, these findings confirm that green concrete is not only a laboratory concept but also a practical, scalable solution for modern construction that is aligned with environmental and policy goals.

Sustainability Outcomes (Integrated Findings)

The sustainability outcomes of green concrete research are significant and multidimensional. One of the most critical achievements is the reduction of CO₂ emissions, primarily realized through clinker substitution with SCMs such as fly ash, slag, and silica fume, and the incorporation of recycled aggregates. This substitution directly lowers the carbon footprint of concrete production while maintaining its structural performance. Resource efficiency is another major benefit, as the use of RCA and industrial or agricultural by-products reduces the consumption of virgin raw materials and diverts large volumes of waste from landfills. These practices not only conserve natural resources but also align

with global sustainability mandates. Lifecycle benefits are evident in the extended durability of green concrete, which minimizes maintenance requirements and replacement cycles, thereby lowering the overall environmental impact of infrastructure. Cost-effectiveness has also been demonstrated, particularly at scale, where green concrete proves economically viable when SCMs and RCA are locally available, reducing transportation and processing costs. Furthermore, the integration of RCA and waste materials supports circular economy principles by closing material loops, promoting reuse, and reinforcing recycling practices in the construction industry. Finally, scalability has been confirmed through case studies documenting the successful mainstream adoption of green concrete in infrastructure projects, provided that strict quality control measures and performance-based standards are followed. Collectively, these outcomes establish green concrete as a sustainable, economically practical, and environmentally responsible alternative to conventional concrete.

FUTURE SCOPE

The future scope of green concrete research and applications is vast, encompassing advanced material development, performance enhancement, sustainability, practical applications, and new research directions. In terms of material innovation, nanotechnology offers exciting opportunities, with nano-silica, nano-clay, and graphene oxide being investigated to refine the microstructure, increase strength, and improve durability. Hybrid SCM blends that combine fly ash, slag, silica fume, and agricultural waste are expected to deliver tailored performance, whereas bio-based additives, such as microbial concrete and biopolymers, may enable self-healing and further sustainability. Performance enhancement remains a critical area, particularly in addressing early-age strength delays in high fly ash mixes using admixtures and innovative curing techniques. Long-term durability studies under extreme conditions, including marine, acidic, and freeze–thaw environments, are essential to validate resilience, and the development of smart concrete systems with embedded sensors will allow real-time monitoring of permeability, durability, and structural health.

From a sustainability perspective, the push toward carbon-neutral concrete is gaining momentum, with net-zero mixes envisioned through maximum clinker substitution and the integration of carbon-capture technologies. Circular economy models will expand through the - large-scale adoption of RCA and industrial/agro waste, closing material loops, and reducing environmental burdens. Standardized LCA metrics for CO₂ and energy footprints are critical to ensure global comparability and policy alignment. Practical applications will scale further, with green concrete being deployed in highways, bridges, and urban housing projects under performance-based specifications. Policy integration is expected to accelerate adoption, with inclusion in building codes, procurement standards, and sustainability certifications. Cost optimization will be achieved through the local sourcing of SCMs and RCA to minimize transport and processing expenses.

Future research should emphasize the importance of long-term field trials to monitor real-world structures over decades and validate laboratory findings under diverse climatic conditions. AI-driven mix design will play a transformative role, using machine learning to predict the optimal proportions for strength, durability, and sustainability outcomes. Finally, global collaboration is essential, with shared datasets, harmonized standards, and coordinated research efforts across regions to accelerate the mainstream adoption of green concrete. Collectively, these pathways highlight that the future of green concrete lies not only in material innovation but also in systemic integration into infrastructure, policy, and sustainability frameworks.

CONCLUSION

In conclusion, the collective body of research confirms that green concrete is a proven and viable alternative to conventional concrete, capable of matching or even exceeding traditional concrete mixes in terms of strength, durability, and sustainability. SCMs, such as fly ash, slag, and silica fume, play an essential role in reducing CO₂ emissions while simultaneously enhancing long-term performance. The incorporation of RCA and other industrial or agricultural waste materials adds further value by lowering landfill burdens and conserving natural resources; however, strict quality control remains critical to ensure consistency. Durability is significantly enhanced through hybrid SCM blends, which improve

resistance to chloride ingress, chemical attack, and permeability, thereby extending the service life. Although workability trade-offs exist—RCA tends to reduce fresh properties, and fly ash improves them—these challenges can be effectively managed through optimized mix design and admixture use. Overall, sustainability outcomes are clear, with substantial reductions in CO₂ emissions and improved resource efficiency and cost-effectiveness demonstrated in multiple case studies. Importantly, practical adoption is already underway, as successful infrastructure projects highlight that green concrete is not only a laboratory innovation but also a scalable solution ready for mainstream use in modern construction.

REFERENCES

1. Cichocki K, Domski J, Katzer J, Ruchwa M. Impact resistant concrete elements with nonconventional reinforcement. *Rocz Ochr Srod.* 2014;16:692-706.
2. Naik TR, Kumar R. Sustainable concrete with industrial and postconsumer by-product materials. In: Sabnis GM, editor. *Green Building with Concrete: Sustainable Design and Construction*. 2nd ed. Boca Raton (FL): CRC Press; 2015. [Chapter 12; DOI: 10.1201/b18613-13].
3. Siddique R, Belarbi R, editors. *Sustainable concrete made with ashes and dust from different sources: materials, properties and applications*. 1st ed. Duxford (UK): Woodhead Publishing; 2021. doi:10.1016/C2020-0-01219-3.
4. Limbachiya MC, Leelawat T, Dhir RK. Use of recycled concrete aggregate in high-strength concrete. *Mater Struct.* 2000;33(9):574-580. doi:10.1007/BF02480538.
5. Ramesh V, Pandulu G, Khanam N, Lian OC. Compressive strength prediction of ecofriendly recycled aggregate concrete: a machine learning approach. *Res Eng Struct Mater.* 2025;11(6):2965-2982. doi:10.17515/resm2025-595me1212rs.
6. Cheruvu R, Rao BK, Reddy MAK. Experimental research on sustained concrete with the partially substitutions of GGBS, fly ash and silica fume as a cementitious material. *J Eng Technol Sci.* 2025;57(5):713-734. doi:10.5614/j.eng.technol.sci.2025.57.5.10.
7. Kumar M, Prashant S, Kamath MV. Enhancing the sustainability of high strength concrete in terms of embodied energy and carbon emission by incorporating sewage sludge and fly ash. *Innov Infrastruct Solut.* 2022;7(4):240. doi:10.1007/s41062-022-00837-5.
8. Mehta PK. Greening of the concrete industry for sustainable development. *Concr Int.* 2002;24(7):23-28.
9. Thomas C, Setién J, Polanco JA, Alaejos P, Sánchez de Juan M. Durability of recycled aggregate concrete. *Constr Build Mater.* 2013;40:1054-1065. doi:10.1016/j.conbuildmat.2012.11.106.